

Electronic Supplementary Information for

Synthesis and Structural Characterization of Zirconium Complexes Supported by Tridentate Pyrrolide-Imino Ligands with pendant *N*-, *O*- and *S*-donor groups and Their Application in Ethylene Polymerization

A. C. Pinheiro,^a S. M. da Silva,^a T. Roisnel,^b E. Kirillov,^c J.-F. Carpentier,^{c,*} Osvaldo L. Casagrande Jr.^{a,*}

^a *Laboratory of Molecular Catalysis, Instituto de Química, Universidade Federal do Rio Grande do Sul, Avenida Bento Gonçalves, 9500, RS, 90501-970 (Brazil). E-mail: osvaldo.casagrande@ufrgs.br*

^b *Institut des Sciences Chimiques de Rennes, Centre de diffraction X, UMR 6226 CNRS-Université de Rennes 1, F-35042 Rennes Cedex, France*

^c *Institut des Sciences Chimiques de Rennes, Organometallics: Materials and Catalysis Dept., UMR 6226 CNRS-Université de Rennes 1, F-35042 Rennes Cedex, France. E-mail: jean-francois.carpentier@univ-rennes1.fr*

Table of contents

Table S1 Crystal data and structure refinement for **3b**.

Figure S1 ORTEP drawing of [Zr{2-(C₄H₃N-2-CH=N)C₂H₄NHPh}(THF)Cl₃] (**3b**).

Figure S2. ¹H NMR spectrum of **2a** (500 MHz, CD₂Cl₂, 25 °C). (* refers to residual solvent) resonances).

Figure S3. ¹³C{¹H} NMR spectrum of **2a** (125 MHz, CD₂Cl₂, 25 °C).

Figure S4. ¹H NMR spectrum of **2b** (500 MHz, CD₂Cl₂, 25 °C).

Figure S5. ¹³C{¹H} NMR spectrum of **2b** (125 MHz, CD₂Cl₂, 25 °C).

Figure S6. ¹H NMR spectrum of **2c** (400 MHz, CD₂Cl₂, 25 °C).

Figure S7. ¹³C{¹H} NMR spectrum of **2c** (100 MHz, CD₂Cl₂, 25 °C).

Figure S8. ¹H NMR spectrum of **2d** (400 MHz, CD₂Cl₂, 25 °C).

Figure S9. ¹³C{¹H} NMR spectrum of **2d** (100 MHz, CD₂Cl₂, 25 °C).

Figure S10. ¹H NMR spectrum of **4a** (500 MHz, CD₂Cl₂, 25 °C).

Figure S11. ¹³C{¹H} NMR spectrum of **4a** (125 MHz, CD₂Cl₂, 25 °C).

Figure S12. DSC trace of polyethylene produced by **2a**/MAO system (60 °C, 5 bar, time = 15 min, [Al/Zr] = 500).

Figure S13. DSC trace of polyethylene produced by **2b**/MAO system (60 °C, 5 bar, time = 15 min, [Al/Zr] = 500).

Figure S14. DSC trace of polyethylene produced by **2c**/MAO system (60 °C, 5 bar, time = 15 min, [Al/Zr] = 500).

Figure S15. DSC trace of polyethylene produced by **2c**/MAO system (60 °C, 5 bar, time = 15 min, [Al/Zr] = 500).

Figure S16. DSC trace of polyethylene produced by **4a**/MAO system (60 °C, 5 bar, time = 15 min, [Al/Zr] = 500).

Table S1 Crystal data and structure refinement for **3b**.

Molecular formula	C ₄₁ H ₃₄ Cl ₂ N ₄ O ₂ Zr
Formula weight (g mol ⁻¹)	776.84
T (K)	150(2)
Crystal system	monoclinic
Space group	P2 ₁ /n
a (Å)	9.5518(2)
b (Å)	23.0867(6)
c (Å)	16.3796(5)
α (°)	90
β (°)	104.2780(10)
γ (°)	90
V (Å ³)	3500.45(16)
Z	4
ρ _{calcd} (g cm ⁻³)	1.474
μ (mm ⁻¹)	0.510
F(000)	1592
Crystal size (mm)	0.38 x 0.13 x 0.12
θ range (°)	2.94 to 27.48
Limiting indices (h, k, l)	-12 ≤ h ≤ 12 -29 ≤ k ≤ 29 -21 ≤ l ≤ 21
Reflections collected	31533
Reflections unique (R _{int})	7995 (0.0513)
Completeness to θ _{max} (%)	99.7
Data / restraints / param.	7995 / 0 / 452
Min. and max. transmission	0.941 and 0.890
R ₁ [I > 2σ(I)]	0.0361
wR ₂ [I > 2σ(I)]	0.0751
R ₁ (all data)	0.0495
wR ₂ (all data)	0.0804
Largest diff. peak and hole (e Å ⁻³)	0.349 and -0.476




Figure S1. ORTEP drawing of $[\text{Zr}\{2-(\text{C}_4\text{H}_3\text{N}-2-\text{CH}=\text{N})\text{C}_2\text{H}_4\text{NHPH}\}(\text{THF})\text{Cl}_3]$ (**3b**) (thermal ellipsoids drawn at the 30% probability level). Selected bond distances (Å) and angles (deg): Zr(1)-N(1) = 2.2169(18), Zr(1)-N(7) = 2.3436(18), Zr(1)-N(21) = 2.2356(17), Zr(1)-N(27) = 2.3461(17), Zr(1)-O(14) = 2.4932(15), Zr(1)-O(34) = 2.5347(14), Zr(1)-Cl(1) = 2.4834(6), Zr(1)-Cl(2) = 2.4729(5), N(1)-Zr(1)-N(21) = 86.75(6), N(1)-Zr(1)-N(7) = 71.56(6), N(21)-Zr(1)-N(7) = 76.15(6), N(1)-Zr(1)-N(27) = 80.06(6), N(21)-Zr(1)-N(27) = 70.68(6), N(7)-Zr(1)-N(27) = 137.13(6), N(1)-Zr(1)-Cl(2) = 96.32(5), N(21)-Zr(1)-Cl(2) = 147.54(5), N(7)-Zr(1)-Cl(2) = 74.28(4), N(27)-Zr(1)-Cl(2) = 141.73(4), N(1)-Zr(1)-Cl(1) = 148.41(5), N(21)-Zr(1)-Cl(1) = 105.41(5), N(7)-Zr(1)-Cl(1) = 139.21(5), N(27)-Zr(1)-Cl(1) = 76.91(4), Cl(2)-Zr(1)-Cl(1) = 88.704(19), N(1)-Zr(1)-O(14) = 135.37(6), N(21)-Zr(1)-O(14) = 74.20(6), N(7)-Zr(1)-O(14) = 64.89(6), N(27)-Zr(1)-O(14) = 127.42(5), Cl(2)-Zr(1)-O(14) = 81.32(4), Cl(1)-Zr(1)-O(14) = 76.20(4), N(1)-Zr(1)-O(34) = 73.99(6), N(21)-Zr(1)-O(34) = 133.43(6), N(7)-Zr(1)-O(34) = 132.24(5), N(27)-Zr(1)-O(34) = 64.52(5), Cl(2)-Zr(1)-O(34) = 77.78(3), Cl(1)-Zr(1)-O(34) = 76.70(4), O(14)-Zr(1)-O(34) = 145.91(5).




Figure S2. ^1H NMR spectrum of **2a** (500 MHz, CD_2Cl_2 , 25 °C). (* refers to the presence of unidentified product(s) that arise from the decomposition of **2a** in solution).




Figure S3. $^{13}\text{C}\{\text{H}\}$ NMR spectrum of **2a** (125 MHz, CD_2Cl_2 , 25 °C).




Figure S4. ^1H NMR spectrum of **2b** (500 MHz, CD_2Cl_2 , 25 °C)




Figure S5. $^{13}\text{C}\{\text{H}\}$ NMR spectrum of **2b** (125 MHz, CD_2Cl_2 , 25 °C)




Figure S6. ^1H NMR spectrum of **2c** (400 MHz, CD_2Cl_2 , 25 °C)




Figure S7. $^{13}\text{C}\{^1\text{H}\}$ NMR spectrum of **2c** (100 MHz, CD_2Cl_2 , 25 °C)




Figure S8. ^1H NMR spectrum of **2d** (400 MHz, CD_2Cl_2 , 25 °C)




Figure S9. $^{13}\text{C}\{^1\text{H}\}$ NMR spectrum of **2d** (100 MHz, CD_2Cl_2 , 25 °C)




Figure S10. ^1H NMR spectrum of **4a** (500 MHz, CD_2Cl_2 , 25 °C)




Figure S11. $^{13}\text{C}\{\text{H}\}$ NMR spectrum of **4a** (125 MHz, CD_2Cl_2 , 25 °C)




Figure S12. DSC trace of polyethylene produced by **2a**/MAO system (60 °C, 5 bar, time = 15 min, [Al/Zr] = 500).




Figure S13. DSC trace of polyethylene produced by **2b**/MAO system (60 °C, 5 bar, time = 15 min, [Al/Zr] = 500).




Figure S14. DSC trace of polyethylene produced by **2c**/MAO system (60 °C, 5 bar, time = 15 min, [Al/Zr] = 500).




Figure S15. DSC trace of polyethylene produced by **2d**/MAO system (60 °C, 5 bar, time = 15 min, [Al/Zr] = 500).




Figure S16. DSC trace of polyethylene produced by **4a**/MAO system (60 °C, 5 bar, time = 15 min, [Al/Zr] = 500).