



2,4-Distyryl- and 2,4,6-Tristyrylpyrimidines Synthesis and Photophysical Properties

Michaela Fecková, Pascal Le Poul, Françoise Robin-Le Guen, Thierry Roisnel, Oldřich Pytela, Milan Klikar, Filip Bureš, Sylvain Achelle

► To cite this version:

Michaela Fecková, Pascal Le Poul, Françoise Robin-Le Guen, Thierry Roisnel, Oldřich Pytela, et al.. 2,4-Distyryl- and 2,4,6-Tristyrylpyrimidines Synthesis and Photophysical Properties. *Journal of Organic Chemistry*, 2018, 83 (19), pp.11712-11726. 10.1021/acs.joc.8b01653 . hal-01880133

HAL Id: hal-01880133

<https://univ-rennes.hal.science/hal-01880133>

Submitted on 28 Sep 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

2,4-Distyryl- and 2,4,6-tristyrylpyrimidines: Synthesis and photophysical properties.

Michaela Fecková,^{†,‡} Pascal le Poul,[†] Françoise Robin-le Guen,[†] Thierry Roisnel,[†] Oldřich

Pytela,[‡] Milan Klikar,[‡] Filip Bureš,^{*,‡} and Sylvain Achelle^{*,†}


[†] Univ Rennes, CNRS, ISCR (Institut des Sciences Chimiques de Rennes) - UMR 6226, F-

35000 Rennes, France. [‡] Institute of Organic Chemistry and Technology, Faculty of Chemical

Technology, University of Pardubice, Studentská 573, Pardubice, 53210, Czech Republic.

Corresponding authors: *E-mails: sylvain.achelle@univ-rennes1.fr; filip.bures@upce.cz

Synopsis TOC



Abstract

The synthesis of a series of twenty new 2,4,6-tristyrylpyrimidines and three new 2,4-distyrylpyrimidines by means of combination of Knoevenagel condensation and Suzuki-Miyaura cross coupling reaction is reported. This methodology enables to obtain chromophores with identical or different substituent on each arm. The photophysical properties of the compounds are described. Optical properties and TD-DFT calculations indicate that photophysical properties of target compounds are mainly affected by the nature of the electron-donating group in C4/C6 positions, except when the C2 substituent is a significantly stronger electron-donating group. However, the C2 substituent has a strong influence on emission quantum yield: addition of a strong electron-donating group tends to decrease the fluorescence quantum yield whereas a moderate electron-withdrawing group results in a significant increase of fluorescence quantum yield.

Introduction

During the past two decades, there has been a great interest in the synthesis of pyrimidine fluorophores.¹ The pyrimidine is a six-membered heterocycle with two nitrogen atoms (1,3-diazine) that exhibits a strong electron-withdrawing character. When the pyrimidine ring is combined with electron-donating fragments via π -conjugated linkers, intramolecular charge transfer (ICT) occurs leading, generally, to a strong emission.¹ Recently, pyrimidine-based thermally activated fluorescent emitters (TADF) have been developed and have been used for high external quantum efficiency organic light-emitting diodes (OLEDs).² 4,6-Distyrylpyrimidines have also been developed as two-photon excitation emitters for biological microscopy³ and photoinitiator for multiphoton lithography.⁴ Due to the electron lone pair of its two nitrogen atoms, the pyrimidine ring can catch protons, coordinate metal cations, and link to various (bio)organic molecules leading to modification of its emission properties. Various pyrimidine chromophores have been used as pH,⁵ metal

cations,⁶ nitroaromatic⁷, and protein⁸ fluorescent sensors. Mixtures of neutral and protonated forms of pyrimidine fluorophores have also been used as white light emitters.⁹ Recently, Kato and coworkers have highlighted the influence of substituent in C2 position on the emission properties of pyrimidine derivatives.¹⁰

Y-shaped centripetal molecules have been subject to intensive research.¹¹ In this context, the triazine core has been extensively used.¹² In these structures, periphery-to-core multidimensional charge transfer lead to large second-order optical response¹³ and large two photon absorption cross section.¹⁴ Numerous 2,4,6-triaryl- and 2,4,6-triarylethynylpyrimidine chromophores have been designed for their luminescence properties.^{15,16}

Styrylpyrimidines are generally obtained by Knoevenagel condensation of an aldehyde with methylpyrimidine under basic or acidic conditions.^{4,5,8,9a,10,17} This reaction can be easily carried out on the methyl group in positions C2, C4 and/or C6. Using this strategy, 2-styryl,¹⁸ 4-styryl^{3c,9a,17} and 4,6-distyrylpyrimidine^{3,4,5a,8,10,17} as well as 4,4',6,6'-tetrastyrylpyrimidine¹⁹ chromophores have been prepared so far; selected known 4,6-distyrylpyrimidines are presented in Chart 1. To the best of our knowledge, only the unsubstituted 2,4,6-tristyrylpyrimidine has been described to date.²⁰




Chart 1. Structures of selected known chromophores 4,6-distyrylpyrimidines.^{5a,17a}

In this contribution, we describe the design and synthesis of 2,4,6-tristyrylpyrimidines and 2,4-distyrylpyrimidines by combining Suzuki-Miyaura cross coupling reaction and Knoevenagel condensation. This strategy enables the synthesis of compounds with different substituents on each arm and, thus, allows modification of their electron donating or withdrawing abilities. The molecular structure obtained by X-ray analysis of a selected

chromophore is also described. The photophysical properties of target chromophores were studied and thoroughly compared with the corresponding 4,6-distyrylpyrimidines. The DFT and TD-DFT calculations were also performed on selected chromophores to rationalize their photophysical properties.


Results and discussion

Synthesis

Various strategies have been considered for the synthesis of 2,4,6-tristyrylpyrimidines. Threefold Knoevenagel condensation from 2,4,6-trimethylpyrimidine has been envisioned. However, the pyrimidine starting material cannot be isolated easily in a good yield.²¹ The synthesis of 2-methyl-4,6-distyrylpyrimidine was also considered by treating 4,6-distyrylpyrimidine with methyllithium followed by *in-situ* rearomatization with DDQ according to known procedure²² but we failed in obtaining the desired product. We therefore proposed a third strategy, starting from commercially available 2-chloro-4,6-dimethylpyrimidine and 2,4-dichloro-6-methylpyrimidine. A combination of Suzuki cross-coupling and Knoevenagel condensation has been developed leading to twenty-one tristyrylpyrimidine chromophores (Schemes 1–2).


Chromophores **2** with identical substituents in C4 and C6 positions were obtained in two steps from 2-chloro-4,6-dimethylpyrimidine. The first step consists of the *in-situ* conversion of arylalkynes into styrylboronic acid by action of catecholborane followed by palladium-catalyzed Suzuki-Miyaura cross coupling reaction.²³ 2-Styrylpyrimidine intermediates **1** were obtained in moderate to good yields. 2,4,6-Tristyrylpyrimidines **2** were obtained by condensation between the C4 and C6 methyl group and the corresponding aromatic aldehyde in boiling aqueous 5 M NaOH using Aliquat 336 as catalyst.^{5a,17a} Moderate to good yields

were generally observed. The lower yields, observed in particular for unsubstituted styryl derivatives, were due to more complicated purification process.




Scheme 1: Synthesis of compounds **2**.

To obtain 2,4,6-tristyrylpyrimidines **5** with three different arms, a three-step synthetic route employed 2,4-dichloro-6-methylpyrimidine as a starting material (Scheme 2). The first step consisted in a C4 regioselective Suzuki-Miyaura cross coupling reaction with *in situ* formed styrylboronic acid leading to intermediates **3**. The observed regioselectivity of cross coupling reaction in C4 over C2 position of the pyrimidine ring is in accordance with the literature.^{15b,16a,24} The second step consisted in a second Suzuki-Miyaura cross coupling reaction in C2 position leading to 2,4-distyrylpyrimidines intermediates **4** and finally a Knoevenagel condensation of 4-(*N,N*-diphenylamino)benzaldehyde on the methyl group in C6 position lead to chromophores **5**.



Scheme 2: Synthesis of compounds 5.

Starting from 2-chloro-4-methylpyrimidine, 2,4-distyrylpyrimidines were obtained in a similar two-step synthetic pathway (Scheme 3).



(i): catecholborane, THF, reflux, 3.5h
 (ii): 2-chloro-4-methylpyrimidine, Pd(PPh₃)₄, Na₂CO₃, reflux, 15h
 (iii): 4-R-C₆H₄-CHO, aliquat 336, NaOHaq 5M, reflux, 3h

Scheme 3: Synthesis of compounds 7.

All new compounds are well soluble especially in chlorinated solvents (DCM, CHCl₃) and were characterized by ¹H, ¹³C NMR and HRMS spectroscopic techniques. The selectivity of the Suzuki-Miyaura cross coupling as well as condensation reactions was sufficiently high to generate all *trans*-isomer within the limits of NMR detection as observed previously.^{5a} The stereochemistry of the double bonds was unequivocally established on the basis of coupling constant for the vinylic proton in the ¹H NMR (*J* ≈ 16 Hz). No *trans/cis* isomerisation were observed during photophysical experiments.

X-ray Analysis

Chromophore **2h** provided crystals for X-ray analysis by slow evaporation of its dichloromethane/ethyl acetate (1/1, v/v) solution. The measured crystal, a large fragment of a large yellow and transparent prism, confirms the proposed molecular structure; in particular the *E* configuration of the three vinylic linkers is confirmed (Figure 1). An orthorhombic crystal system is observed with a Pna2₁ space group. The presence of a (modelled) disorder

on one of the two C4/C6 arm, already observed for similar structures,^{19b} can be shown. Solid state supramolecular assembly of the chromophore revealed an orthorhombic crystal system with a Pna2₁ space group. The crystal structure shows that the angles between the planes of three benzene rings and the pyrimidine central core lower than 20°, indicating that they are not completely planar, in accordance with other 4-styryl- and 4,6-distyrylpyrimidines.^{9a,25} It should be noted that the dihedral angle between the phenyl ring in C2 position and the pyrimidine core is the lowest (~7°). Bond length alternation (BLA) were calculated for the vinylic linker on each arm and were revealed to be slightly lower for the C2 arm (0.1185 Å), than for C4/C6 arms (0.1205, 0.1600 and 0.1775 Å) indicating that the C2 arm imparts stronger ICT.




Figure 1: ORTEP drawing of the chromophore **2h** with thermal ellipsoid at 50%.

Thermal properties

Thermal behaviour of the final compounds **2**, **5** and **7** as well as compounds **A₂** and **A₃** was studied by differential scanning calorimetry (DSC). Figure 2 shows thermograms of representative compounds **2i**, **2m**, **A₂** and **A₃** while Table 1 lists all measured melting points (T_m) and temperatures of thermal decompositions (T_d). All DCS curves are given in the SI. The measured melting points range from 128 to 243 °C. The temperature of decomposition was estimated within the range of 195-320 °C. Further discussion on the thermal properties is provided in the SI.




Figure 2: Representative DSC thermographs of compounds **2i**, **2m**, **A₂** and **A₃** obtained with a scanning rate of 3°C/min in the range 50-400°C

Table 1: DSC results for chromophores **2**, **5**, **7**, **A₂** and **A₃**.

Comp.	T_m (°C)	T_d (°C)	Comp.	T_m (°C)	T_d (°C)	Comp.	T_m (°C)	T_d (°C)	Comp.	T_m (°C)	T_d (°C)
2a	193	300	2h	200	295	2o	/	250	7a	137	290
2b	128	290	2i	/	250	2p	/	220	7b	185	305
2c	/	245	2j	/	240	2q	/	280	7c	243	265
2d	/	305	2k	/	310	2r	210	265	7d	/	250
2e	183	305	2l	/	195	2s	/	300	A₂	191	260
2f	/	250	2m	/	310	5a	/	240	A₃	205	320
2g	/	270	2n	/	290	5b	/	210			

T_m = melting point (the point of intersection of a baseline and a tangent of thermal effect = onset). T_d = thermal decomposition (pyrolysis in N₂ atmosphere).

Common feature of tripodal (D- π)₃-A or (D- π)₂-A-(π -A) chromophores **2a-s** and **5a-b** is their resistance to crystallize and they often occur as solid glasses and amorphous solid. This suggests a more sophisticated thermal behaviour of centripetal star-shaped systems. Hence, their DSC curves are frequently similar and decorated by solid-solid or glass transitions. Based on the DSC analysis there are no evident general trends between type or position of particular donor used and thermal behavior of tripodal chromophores. Structural

modifications (donor variation) often influences the thermal properties of tripodal chromophores only negligibly because the intrinsic nature of these molecules remains the same.

In general, 2,4- and 4,6-disubstituted pyrimidines (**7a–d**, **A₂** and **A₃**) have demonstrated a similar thermal behaviour. A presence of donor groups (NMe₂, OMe) in quadrupolar molecules **7b** and **7c** increases the melting point up to 100 °C compared to “donor free” analogue **7a**.

The *T_d* of tripodal molecules **2i/2m** and their quadrupolar analogous **A₂/A₃** are comparable (Figure 2) and dictated by the type of attached donors on the periphery. Therefore, DMA **2i/A₂** and TPA analogous **2m/A₃** have demonstrated almost identical *T_d* values (250/260 and 310/320 °C, see Table 1).

Photophysical properties

The UV/Vis and photoluminescence (PL) spectroscopic data of compounds **2**, **5** and **7** measured in CH₂Cl₂ at room temperature are presented in Table 2. The analyses were carried out by using low concentrations of chromophores ($0.5\text{--}1.5 \times 10^{-5}$ M). To facilitate comparison of photophysical properties, 4,6-distyrylpyrimidines **A^{5a}** were also included in Table 1. As an example, the spectra of compounds **2b**, **2c** and **2d** are provided in Figure 3.




Figure 3: Normalized absorption (solid lines) and emission spectra (dashed lines) of compounds **2b** (black), **2c** (green) and **2d** (green) in CH₂Cl₂ solution.

For all the compounds, the less energetic absorption band ($\lambda_{\text{max}} = 312\text{--}429$ nm) is attributed to charge transfer. Except compounds **2a**, **2h**, **7a** and **7b**, that are however slightly emissive in non polar heptane, all the compounds exhibit significant emission. In case of **2h**, the absence of emission is attributed to twisted intramolecular charge transfer excited state. For these compounds, as generally observed for pyrimidine push-pull chromophores,¹ large Stokes shifts were obtained, indicating large difference (vibrational, electronic, geometric) between the Franck-Condon state and the excited state. For tristyrilpyrimidines **2** and **5**, the position of absorption and emission wavelength maxima depends mainly on C4/C6 substituents. However, it should be noted that a significant red-shift in emission is observed when the C2

substituent is a significantly stronger electron-donating groups than C4/C6 substituents (**2j** and **2k**). Whereas the ICT generally occurs over the C4/C6 arm, in this case, the ICT is probably prevailing on the C2 arm. The fluorescence quantum yield varies significantly when the C2 substituent is modified. When tristyrylpyrimidines **2b-2d** with unsubstituted styryl group in C2 position are compared with 2,6-distyrylpyrimidines **A1-A3**, it appears that the addition of the styryl group in C2 position leads to a slight red shift of the emission maxima and a significant increase of the fluorescence quantum yield. The presence of an electron-donating group (methoxy, dimethylamino or diphenylamino) on the C2 arm (compounds **2e-2g**, **2i**, **2l**, **2m**) results in a slight blue shift of emission regarding the corresponding unsubstituted styryl derivatives **2b-2d**. The opposite trend is observed for **2j** and **2k** probably due to change in the ICT direction over the C2 arm. Whereas chromophores with dimethylamino group on C4/C6 arms (compounds **A2**, **2c**, **2f**, **2l**, **2o**, **2r** and **5a**) are generally highly luminescent, the incorporation of this fragment on C2 (chromophores **2h-2j**, **5b** and **7c**) leads to a dramatic decrease of fluorescence quantum yield. On the other hand, the addition of a trifluoromethyl fragment, a moderately electron-withdrawing group, on C2 arm (chromophores **2q-2s**) results in a significant increase of the fluorescence quantum yield up to 1.00 for **2s**. 2,4-Distyrylpyrimidines **7** exhibits significantly blue shifted absorption and emission with regards to their 4,6-distyryl and 2,4,6-tristyrylpyrimidines analogues. All these trends are in accordance with the observation made on arylpyrimidine series.^{1a,15a-b}

Table 2: UV/Vis and PL data in CH₂Cl₂.

Compd ^a	UV/vis λ_{max} , nm	PL		Stokes shift
	(ϵ , mM ⁻¹ ·cm ⁻¹)	λ_{max} , nm	Φ_F^b	cm ⁻¹
A1 ^{17a}	359 (36.0)	439	-	5076
A2 ^{5a}	429 (42.1)	530	0.40	4442
A3 ^{5a}	427 (47.6)	540	0.55	4901

2a	312 (74.3)	—	—	—
2b	369 (35.9)	442	0.10	4476
2c	423 (48.1)	537	0.72	5019
2d	430 (55.0)	551	0.78	5107
2e	339 (64.0)	439	0.15	6719
2f	423 (45.6)	533	0.53	4879
2g	424 (68.9)	543	0.91	5168
2h	370 (94.0)	—	—	—
2i	402 (97.3)	536	0.22	6219
2j	409 (112.9)	577	0.03	7118
2k	376 (61.7)	558	0.10	7799
2l	406 (42.4)	533	0.59	5869
2m	415 (86.2)	544	0.56	5714
2n	347 (61.6)	443	0.11	6245
2o	418 (52.5)	536	0.52	5266
2p	424 (69.7)	544	0.75	5202
2q	370 (26.8)	441	0.21	4351
2r	429 (49.1)	545	0.72	4961
2s	430 (60.4)	554	1.00	5205
5a	420 (40.4)	549	0.68	5595
5b	386 (58.1)	548	0.02	7659
7a	305 (41.3)	—	—	—

7b	331 (53.9)	—	—	—
7c	395 (67.2)	493	0.04	5032
7d	402 (45.5)	527	0.72	5900

^a All spectra were recorded at room temperature at $c = 0.5 \times 10^{-5}$ M to 1.5×10^{-5} . ^b Fluorescence quantum yield ($\pm 10\%$) determined relative to 9,10-bisphenylethynylanthracene in cyclohexane ($\Phi_F = 1.00$).²⁶

In order to gain further insights into the photophysical properties of these compounds, their absorption and emission behavior was studied in a variety of aprotic solvents. While the absorption maxima were not significantly shifted, an increase in solvent polarity, estimated by Dimroth-Reichardt polarity parameter,²⁷ led to bathochromic shifts of the emission maxima. The results of emission solvatochromism are summarized in Table 3. As an example, the spectra registered for compound **2g** are shown in Figure 4 and the change in emission color under UV irradiation for compound **2k**, easily seen by the naked eye, can be seen in Figure 5. This solvatochromic behavior, characteristic for fluorophore featuring intramolecular charge transfer, can be explained by the stabilization of the highly polar emitting state by polar solvents.²⁸ For all the compounds, the emission maxima were plotted *versus* Dimroth-Reichardt polarity parameter (see Figures S106-S112) and, in all cases, a good linearity was observed. The emission solvatochromic behavior can be quantified by the slope of the corresponding regression line. Once again, with the exception of compound **2k**, the substituents in C4/C6 arm are the most affected by the emission solvatochromism with decreasing order: $\text{NMe}_2 > \text{NPh}_2 > \text{OMe}$. This is in accordance to the electron-donating strength of the substituents. The slopes for 2,4-distyrylpyrimidines **7c** and **7d** are significantly lower than that of their 2,4,6-tristyrylpyrimidine analogues **2i** and **2m**, indicating that both arms in C4 and C6 position play a role on the emission solvatochromism and, therefore on ICT into the chromophores.

Table 3: Emission solvatochromism of pyrimidine derivatives in various aprotic solvents.

Compd	Heptane $E_T(30)^a = 30.9$ $\lambda_{\max}$, nm	Toluene $E_T(30)^a = 33.9$ $\lambda_{\max}$, nm	THF $E_T(30)^a = 37.4$ $\lambda_{\max}$, nm	CH_2Cl_2 $\Delta E_T(30)^a = 40.7$ $\lambda_{\max}$, nm	Acetone $\Delta E_T(30)^a = 42.2$ $\lambda_{\max}$, nm	MeCN $\Delta E_T(30)^a = 45.6$ $\lambda_{\max}$, nm	DMSO $\Delta E_T(30)^a = 45.1$ $\lambda_{\max}$, nm
2b	397, 420	408, 429	432	442	450	470	471
2c	453	483	526	537	563	587	601
2d	464	482	520	551	563	591	596
2e	402, 421	410, 433	432	439	440	453	461
2f	450	480	522	533	559	581	598
2g	461	480	515	543	555	583	584
2i	450	479	521	536	558	577	601
2j	460	495	512	547	552	574	577
2k	439	466	511	558	572	627	622
2l	451	480	521	533	561	584	596
2m	460	479	514	544	555	589	586
2n	401, 422	411, 433	433	443	445	463	471
2o	449	480	520	536	565	586	597
2p	460	479	519	544	558	586	585
2q	398	411	436	441	452	463	475
2r	456	486	533	545	565	587	592
2s	467	486	526	554	567	600	599
5a	457	491	542	549	571	594	589
5b	398	411	436	441	452	463	475
7c	433	455	484	493	523	513	527
7d	447	470	502	527	531	546	547

^a Dimroth–Reichardt polarity parameter, $\text{kcal}\cdot\text{mol}^{-1}$




Figure 4: Normalized emission spectra of **2g** in different aprotic solvents.




Figure 5: Fluorescence color changes experienced by **2k** in various solvents. Picture was taken in the dark upon irradiation with a hand-held UV lamp ($\lambda_{\text{em}} = 366 \text{ nm}$).

The ability of protonation of pyrimidine chromophores has been already demonstrated.^{5,9} Generally, the protonation of amino-substituted stryrylpyrimidines results in quenching of emission; however, in the case of less electron-donating substituents, such as methoxy groups,

the protonation lead to a red-shifted emission.^{5a,9a} The changes in the emission spectra of **2q** upon addition of (1*S*)-(+)-10-camphorsulfonic acid are illustrated in Figure 6. The progressive disappearance of the emission band of the neutral form at 441 nm is observed, whereas a new red-shifted absorption band at 540 nm progressively appear corresponding to the monoprotonated species.^{9a} As shown on Figure 7, the neutral form of **2q** emits dark blue light under UV-irradiation whereas the protonated form emits green light. A mixture of the two forms enables to obtain cyan light.




Figure 6 Changes in the emission spectra of a CH₂Cl₂ solution of **2q** ($c = 0.9642 \times 10^{-5}$ M) upon addition of (1*S*)-(+)-10-camphorsulfonic acid (0.1 – 50 eq.). $\lambda_{\text{exc}} = 380$ nm.




Figure 7 Change in the color of a CH_2Cl_2 solution of **2q** ($c = 0.9642 \times 10^{-5} \text{ M}$) after the addition of 0.8 equiv (middle) and 50 equiv of (1*S*)-(+)-10-camphorsulfonic acid (right). Picture was taken in the dark upon irradiation with a hand-held UV lamp ($\lambda_{\text{em}} = 366 \text{ nm}$).

DFT calculations

DFT calculations implemented in Gaussian 16 software package²⁹ were employed to investigate the fundamental properties of representative pyrimidines **A3**, **2g**, **2j**, **2k**, and **2m** with a systematically varied structural arrangement. Their optimized geometries, the HOMO/LUMO energies, and ground state dipole moments μ (Table 4) were obtained by DFT B3LYP/6-311+g(2d,p) method. The calculated HOMO/LUMO levels were further visualized in the energy level diagram as shown in Figure 8. Whereas the HOMO-LUMO gaps of all molecules are almost identical (2.97-3.02 eV), the principal variations are seen at both HOMO/LUMO levels. Hence, decoration of the central pyrimidine acceptor with two or three donor arms affects the position of the HOMO and LUMO rather than the HOMO-LUMO difference. This is in accordance to our latest observation and generalization on multipodal chromophores.³⁰ The frontier molecular orbitals are further visualized in Figure 9. In the parent molecule **A3**, the HOMO is localized on both *N,N*-diphenylamino donors but is also

mixed with the LUMO spread over the central pyrimidine and adjacent π -linkers. This implies lower charge separation. The situation is similar in **2g** bearing weak additional 4-methoxystyryl donor appended at C2 (the second *N,N*-diphenylamino donor is occupied by the HOMO-1). However, by attaching strong electron releasing moieties, such as *N,N*-dimethylamino or *N,N*-diphenylamino groups, the HOMO has completely moved on the arms appended at C2 regardless what type of donors are connected at C4/C6. Hence, for **2j**, **2k**, and **2m**, the ICT dominates from the arm connected at pyrimidine C2.

Table 4: DFT calculated data of representative chromophores.

Compd ^a	E_{HOMO} eV	E_{LUMO} eV	ΔE eV	μ D	λ_{max} nm/eV
A₃	-5.26	-2.27	2.99	3.39	475/2.61
2g	-5.21	-2.19	3.02	2.00	468/2.65
2j	-5.09	-2.12	2.97	1.41	458/2.71
2k	-5.14	-2.13	3.01	3.89	403/3.08
2m	-5.14	-2.21	2.94	1.60	464/2.67




Figure 8 Energy level diagram of the DFT-derived HOMO/LUMO energies.




Figure 9 Optimized geometries and HOMO (red) and LUMO (blue) localizations in representative chromophores.

The electronic absorption spectra of representative chromophores were further calculated using TD-SCF (nstates = 10) B3LYP/6-311+g(2d,p) method. The spectra are listed in Figure S113 jointly with the experimental data; the calculated longest-wavelength absorption maxima are given in Table 3. Their correlation with the experimental λ_{max} values is very tight

as shown in Figure S114. This implies that, despite the calculated values are generally red-shifted, the employed method is capable to described trends within the given series of molecules. The spectra of representative chromophores feature a low energy lying CT-band with the λ_{max} appearing between 403-475 nm (376-428 nm experimentally). Compared to tripodal molecules **2**, the quadrupolar chromophore **A3** showed the most bathochromically shifted CT-band ($\lambda_{\text{max}} = 428$ nm). This may be explained by the Frenkel exciton model, which predicts splitting of the singlet excited state into two and three bands for quadrupolar and tripodal molecules, as compared to their linear analogue. Whereas for quadrupolar molecules is the low energy band dominant, the low energy lying two states of a tripodal molecule are degenerate while the third high energy state has zero oscillator strength. Hence, the absorption spectra of both types of molecules are characterized by a single CT-band, eventually accompanied by a shoulder for quadrupolar molecules and a blue-shift for tripodal ones. According to the performed calculations, the CT-bands of quadrupolar **A3** and tripodal **2g**, bearing weak methoxy electron donor, are almost exclusively generated by the HOMO→LUMO transition. On the other hand, the CT bands of **2j** and **2m**, bearing all amino donors, are dominated by the HOMO→LUMO, HOMO-1→LUMO, and HOMO→LUMO+1 transitions. Replacement of two amino donors at C4/C6 as in **2k** led to a significantly red-shifted HOMO→LUMO transition (~468 nm, see Figure S113) but with diminished oscillator strength. Hence, the observed CT-band is generated by the HOMO→LUMO+1 and HOMO-1→LUMO transitions.

Conclusions

In conclusion, we have successfully synthesized 2,4,6-tristyrylpyrimidine and 2,4-distyrylpyrimidine chromophores with identical or different substituent on each arm. In terms of absorption and emission maxima, and calculated HOMO-LUMO gaps, 2,4,6-tristyrylpyrimidines exhibits generally the similar properties as the corresponding 4,6-

distyrylpyrimidines. Nevertheless, when the C2 substituent is a significantly stronger electron-donating substituents than C4/C6 ones, the ICT occurs mainly on this branch and dictates the photophysical properties. In all cases, the C2 substituent play a key role on the emission quantum yield. As one would expected, all these materials exhibit strong emission solvatochromism and pH sensibility. Comparison of the two-photon absorption properties of 2,4,6-tristyrylpyrimidine with the corresponding 4,6-distyrylpyrimidines are currently under investigation.

Experimental Section

General Conditions. In air- and moisture-sensitive reactions, all glassware was flame-dried and cooled under nitrogen. Thermal behavior of the target compounds was measured in open aluminous crucibles under N₂ inert atmosphere. DSC curves were determined with a scanning rate of 3 °C/min within the range 25–400 °C. NMR spectra were acquired at room temperature. Chemical shifts are given in parts per million relative to TMS (¹H, 0.0 ppm) and CDCl₃ (¹³C, 77.0 ppm). Acidic impurities in CDCl₃ were removed by treatment with anhydrous K₂CO₃. High resolution MALDI MS spectra were measured on a MALDI mass spectrometer equipped with nitrogen UV laser (337 nm, 60 Hz) and quadrupole analyser (positive-ion mode over a normal mass range (m/z 50-2000) with resolution 100 000 at m/z = 400). *Trans*-2-[3-(4-*tert*-butylphenyl)-2-methyl-2-propenylidene]malononitrile (DCTB) was used as a matrix. Mass spectra were averaged over the whole MS record for all measured samples. UV-vis and fluorescence spectra were recorded using standard 1 cm quartz cells. Compounds were excited at their absorption maxima (band of lowest energy) to record the emission spectra. The Φ_F values were calculated using a well-known procedure with 9,10-diphenylethynylanthracene in cyclohexane as standard.²⁶ Stokes shifts were calculated by considering the lowest energetic absorption band. All calculations were carried out in Gaussian 09W package at the DFT level of theory. The initial geometry optimizations were carried out by the PM3 method implemented in program ArgusLab and subsequently by the DFT B3LYP method using the 6-311G++(2d,f,p) basic

set. The energies of the HOMO and LUMO (E_{HOMO} and E_{LUMO}), their differences (ΔE) and ground state dipole moments (μ) were calculated by the DFT B3LYP/6-311++G(2d,f,p) method.

General procedure for Suzuki-Miyaura cross-coupling reaction. The corresponding acetylene (1.57 equiv) was dissolved in THF (20 mL) and nitrogen was bubbled through the solution for 10 min. Catecholborane (1.9 equiv of 1 M solution in THF) was added and the reaction mixture was heated to reflux for 1.5 h. The second portion of catecholborane (0.7 equiv) was added and heating was continued for 2 h. The reaction mixture was cooled to room temperature and $\text{Pd}(\text{PPh}_3)_4$ (0.025 equiv) and corresponding pyrimidine (1 equiv) were added. Solution was stirred for 20 min before 20% aqueous Na_2CO_3 (5 mL) was added and the mixture was stirred under nitrogen at reflux for 15 h. The reaction mixture was cooled and then diluted with CH_2Cl_2 (20 mL). The organic layer was washed with water (3x20 mL), then with brine (20 mL), separated, dried over MgSO_4 and the solvents were evaporated under reduced pressure. The crude product was purified by column chromatography (SiO_2 , indicated solvents).

General procedure for Knoevenagel condensation. Aldehyde (1 equiv) and corresponding 4-methylpyrimidine (1 equiv) or 4,6-dimethylpyrimidine (0.5 equiv) were added in 5 M aqueous NaOH (15 mL) containing Aliquat 336 (0.1 equiv). Solution was heated to reflux for 3 h and then cooled to room temperature. The precipitate was filtered off, washed with water, and purified by recrystallization from $\text{CH}_2\text{Cl}_2/n$ -heptane and/or by column chromatography (SiO_2 , indicated solvents).

(*E*)-2-Styryl-4,6-dimethylpyrimidine (1a). Synthesized from phenylacetylene (161 mg, 1.57 mmol) and 2-chloro-4,6-dimethylpyrimidine (143 mg, 1 mmol) following the general procedure for Suzuki-Miyaura reaction. The crude product was purified by column chromatography (SiO_2 , petroleum ether:EtOAc, 7:3). Yield: 78 mg (37 %); white solid. R_f : 0.7 (SiO_2 ; petroleum ether:EtOAc, 7:3). Mp: 47.5–49.4 °C (lit.³¹ 47–50°C). ^1H NMR (300

MHz, CDCl₃): δ = 2.50 (s, 6H), 6.86 (s, 1H), 7.21 (d, 3J = 15.9 Hz, 1H), 7.29–7.41 (m, 3H), 7.61–7.64 (m, 2H), 7.97 (d, 3J = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 24.1, 117.7, 127.7, 127.9, 128.8, 128.9, 136.4, 137.6, 164.3, 166.6 ppm. IR (ATR): ν = 3057, 1533, 1367, 978, 747, 692 cm⁻¹. HR-MALDI-MS (DCTB): m/z calculated for C₁₄H₁₅N₂ [(M+H)⁺] 211.1230, found 211.1227.

(E)-2-(4-Methoxystyryl)-4,6-dimethylpyrimidine (1b). Synthesized from 4-ethynylanisole (415 mg, 3.14 mmol) and 2-chloro-4,6-dimethylpyrimidine (286 mg, 2 mmol) following the general procedure for Suzuki-Miyaura reaction. The crude product was purified by column chromatography (SiO₂, petroleum ether:EtOAc, 7:3). Yield: 257 mg (54 %); brownish solid. *R*_f: 0.4 (SiO₂; petroleum ether:EtOAc, 7:3). Mp: 87.9–90.2 °C. ¹H NMR (300 MHz, CDCl₃): δ = 2.48 (s, 6H), 3.82 (s, 3H), 6.82 (s, 1H), 6.89–6.92 (m, 2H), 7.07 (d, 3J = 15.9 Hz, 1H), 7.54–7.57 (m, 2H), 7.92 (d, 3J = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 24.1, 55.4, 114.3, 117.4, 125.6, 129.1, 129.2, 137.3, 160.4, 164.6, 166.6 ppm. IR (ATR): ν = 3004, 1574, 1511, 1242, 1178, 1028, 981, 839, 818, 770 cm⁻¹. HR-MALDI-MS (DCTB): m/z calculated for C₁₅H₁₆N₂O [M⁺] 240.1257, found 240.1256.

(E)-2-(4-Dimethylaminostyryl)-4,6-dimethylpyrimidine (1c). Synthesized from 4-ethynyl-*N,N*-dimethylaniline (362 mg, 2.50 mmol) and 2-chloro-4,6-dimethylpyrimidine (230 mg, 1.61 mmol) following the general procedure for Suzuki-Miyaura reaction. The crude product was purified by column chromatography (SiO₂, petroleum ether:EtOAc, 7:3). Yield: 244 mg (59 %); yellow solid. *R*_f: 0.6 (SiO₂; petroleum ether:EtOAc, 7:3). Mp: 112.8–115.2 °C. ¹H NMR (300 MHz, CDCl₃): δ = 2.47 (s, 6H), 3.00 (s, 6H), 6.69–6.72 (m, 2H), 6.78 (s, 1H), 7.01 (d, 3J = 15.9 Hz, 1H), 7.51–7.54 (m, 2H), 7.91 (d, 3J = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 24.2, 40.4, 112.2, 116.9, 123.2, 124.6, 129.1, 138.0, 151.0, 165.1, 166.4 ppm. IR (ATR): ν = 2919, 1580, 1443, 1356, 1165, 986, 820, 748 cm⁻¹. HR-MALDI-MS (DCTB): m/z calculated for C₁₆H₁₉N₃ [M⁺] 253.1574, found 253.1562.

(E)-2-(4-Diphenylaminostyryl)-4,6-dimethylpyrimidine (1d). Synthesized from 4-ethynyl-*N,N*-diphenylaniline (790 mg, 2.94 mmol) and 2-chloro-4,6-dimethylpyrimidine (267 mg, 1.87 mmol) following the general procedure for Suzuki-Miyaura reaction. The crude product was purified by column chromatography (SiO₂, petroleum ether:EtOAc, 8:2). Yield: 200 mg (28 %); yellow solid. *R*_f: 0.4 (SiO₂; petroleum ether:EtOAc, 8:2). Mp: 132.7–135.7 °C. ¹H NMR (300 MHz, CDCl₃): δ = 2.49 (s, 6H), 6.83 (s, 1H), 7.02–7.14 (m, 9H), 7.25–7.30 (m, 4H), 7.46–7.49 (m, 2H), 7.91 (d, ³*J* = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 24.1, 117.3, 122.6, 123.5, 125.1, 125.6, 128.6, 129.4, 129.9, 137.3, 147.4, 148.6, 164.6, 166.5 ppm. IR (ATR): ν = 3030, 1585, 1488, 1273, 749, 692 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₂₆H₂₃N₃ [M⁺] 377.1887, found 377.1888.

(E)-2-[(6-Methoxynaphthalen-2-yl)ethenyl]-4,6-dimethylpyrimidine (1e). Synthesized from 2-ethynyl-6-methoxynaphthalene (286 mg, 1.57 mmol) and 2-chloro-4,6-dimethylpyrimidine (143 mg, 1 mmol) following the general procedure for Suzuki-Miyaura reaction. The crude product was purified by column chromatography (SiO₂, petroleum ether:EtOAc, 7:3). Yield: 230 mg (79 %); yellowish solid. *R*_f: 0.3 (SiO₂; petroleum ether:EtOAc, 7:3). Mp: 133.5–134.9 °C. ¹H NMR (300 MHz, CDCl₃): δ = 2.45 (s, 6H), 3.86 (s, 3H), 6.75 (s, 1H), 7.06–7.13 (m, 2H), 7.26 (d, ³*J* = 15.9 Hz, 1H), 7.66–7.77 (m, 3H), 7.88 (s, 1H), 8.09 (d, ³*J* = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 24.0, 55.3, 105.9, 117.4, 119.1, 124.4, 127.0, 127.3, 128.4, 128.9, 129.9, 131.7, 134.9, 137.7, 158.2, 164.3, 166.4 ppm. IR (ATR): ν = 2931, 1582, 1364, 1163, 1027, 860, 803, 665 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₁₉H₁₈N₂O [M⁺] 290.1414, found 290.1414.

(E)-2-(4-Trifluoromethylstyryl)-4,6-dimethylpyrimidine (1f). Synthesized from 4-trifluoromethylphenylacetylene (426 mg, 2.50 mmol) and 2-chloro-4,6-dimethylpyrimidine (228 mg, 1.59 mmol) following the general procedure for Suzuki-Miyaura reaction. The crude product was purified by column chromatography (SiO₂, petroleum ether:EtOAc, 7:3). Yield:

222 mg (50 %); yellowish solid. R_f : 0.4 (SiO₂; petroleum ether:EtOAc, 7:3). Mp: 94.9–96.5 °C. ¹H NMR (300 MHz, CDCl₃): δ = 2.50 (s, 6H), 6.89 (s, 1H), 7.26 (d, ³ J = 15.9 Hz, 1H), 7.60–7.71 (m, 4H), 7.97 (d, ³ J = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 24.1, 118.2, 124.2 (q, ¹ J_{CF} = 270 Hz), 125.8 (q, ³ J_{CF} = 4 Hz), 127.7, 130.4, 130.5 (q, ² J_{CF} = 32 Hz), 135.8, 139.9 (d, ⁴ J_{CF} = 1 Hz), 163.7, 166.8 ppm. IR (ATR): ν = 2929, 1583, 1319, 1103, 1064, 831, 714 cm⁻¹. HR-MALDI-MS (DCTB): m/z calculated for C₁₅H₁₄F₃N₂ [(M+H)⁺] 279.1104, found 279.1102.

(*E,E,E*)-2,4,6-Tristyrylpyrimidine (2a). Synthesized from **1a** (300 mg, 1.43 mmol) and benzaldehyde (303 mg, 2.85 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by column chromatography (SiO₂, petroleum ether:EtOAc, 9:1) and then by recrystallization from CH₂Cl₂/*n*-heptane. Yield: 155 mg (28 %); white solid. R_f : 0.4 (SiO₂; petroleum ether:EtOAc, 9:1). Mp: 193 °C (lit.^{20b} 197-199°C). ¹H NMR (300 MHz, CDCl₃): δ = 7.08–7.16 (m, 3H), 7.28–7.43 (m, 10H), 7.62–7.69 (m, 6H), 7.93 (d, ³ J = 15.9 Hz, 2H), 8.11 (d, ³ J = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 113.7, 126.5, 127.7, 127.8, 128.3, 128.8, 128.9, 129.3, 136.0, 136.4, 136.7, 137.9, 162.9, 164.6 ppm. All the atoms of carbon were not observed. IR (ATR): ν = 3025, 1635, 1564, 1514, 1368, 963, 739, 689 cm⁻¹. HR-MALDI-MS (DCTB): m/z calculated for C₂₈H₂₃N₂ [(M+H)⁺] 387.1856, found 387.1855.

(*E,E,E*)-2-Styryl-4,6-bis(4-methoxystyryl)pyrimidine (2b). Synthesized from **1a** (78 mg, 0.37 mmol) and 4-methoxybenzaldehyde (102 mg, 0.74 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by column chromatography (SiO₂, petroleum ether:EtOAc, 8:2) and then by recrystallization from CH₂Cl₂/*n*-heptane. Yield: 40 mg (24 %); yellowish solid. R_f : 0.4 (SiO₂; petroleum ether:EtOAc, 8:2). Mp: 128 °C. ¹H NMR (300 MHz, CDCl₃): δ = 3.86 (s, 6H), 6.93–7.01 (m, 6H), 7.11 (s, 1H), 7.29–7.44 (m, 4H), 7.58–7.61 (m, 4H), 7.68–7.70 (m, 2H), 7.89 (d, ³ J =

15.9 Hz, 2H), 8.11 (d, $^3J = 15.9$ Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): $\delta = 55.5, 113.2, 114.5, 124.4, 127.8, 128.5, 128.9, 128.90, 128.91, 129.2, 136.2, 136.6, 137.6, 160.7, 163.1, 164.5$ ppm. IR (ATR): $\nu = 2837, 1604, 1560, 1501, 1251, 1171, 1152, 967, 749$ cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{30}\text{H}_{27}\text{N}_2\text{O}_2$ $[(\text{M}+\text{H})^+]$ 447.2067, found 447.2064.

(*E,E,E*)-2-Styryl-4,6-bis(4-dimethylaminostyryl)pyrimidine (2c). Synthesized from **1a** (150 mg, 0.71 mmol) and 4-*N,N*-dimethylaminobenzaldehyde (213 mg, 1.43 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by column chromatography (SiO_2 , petroleum ether:EtOAc, 8:2) and then by recrystallization from $\text{CH}_2\text{Cl}_2/n$ -heptane. Yield: 63 mg (17 %); black solid. R_f : 0.2 (SiO_2 ; petroleum ether:EtOAc, 8:2). T_d : 245 °C. ^1H NMR (300 MHz, CDCl_3): $\delta = 3.03$ (s, 12 H), 6.71–6.74 (m, 4H), 6.91 (d, $^3J = 15.9$ Hz, 2H), 7.08 (s, 1H), 7.28–7.35 (m, 4H), 7.53–7.56 (m, 4H), 7.68–7.70 (m, 2H), 7.86 (d, $^3J = 15.9$ Hz, 2H), 8.10 (d, $^3J = 15.9$ Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): $\delta = 40.4, 112.2, 112.4, 114.2, 114.7, 121.9, 124.3, 127.8, 128.7, 128.8, 129.2, 136.8, 137.2, 151.2, 163.4, 164.3$ ppm. IR (ATR): $\nu = 2892, 1602, 1555, 1503, 1363, 1162, 965, 800, 746$ cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{32}\text{H}_{32}\text{N}_4$ $[\text{M}^+]$ 472.2622, found 472.2620.

(*E,E,E*)-2-Styryl-4,6-bis(4-diphenylaminostyryl)pyrimidine (2d). Synthesized from **1a** (300 mg, 1.43 mmol) and 4-*N,N*-diphenylaminobenzaldehyde (780 mg, 2.85 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by column chromatography (SiO_2 , petroleum ether:EtOAc, 9:1) and then by recrystallization from $\text{CH}_2\text{Cl}_2/n$ -heptane. Yield: 220 mg (21 %); yellow solid. R_f : 0.4 (SiO_2 ; petroleum ether:EtOAc, 9:1). T_d : 305 °C. ^1H NMR (300 MHz, CDCl_3): $\delta = 6.98$ (d, $^3J = 15.9$ Hz, 2H), 7.05–7.17 (m, 17H), 7.27–7.43 (m, 12H), 7.48–7.51 (m, 4H), 7.67–7.70 (m, 2H), 7.87 (d, $^3J = 15.9$ Hz, 2H), 8.10 (d, $^3J = 15.9$ Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): $\delta = 113.1, 122.5, 123.8, 124.4, 125.2, 127.8, 128.6, 128.77, 128.85, 128.88, 129.56, 129.59, 136.1, 136.6,$

137.6, 147.3, 149.0, 163.1, 164.6 ppm. IR (ATR): ν = 3033, 1559, 1490, 1274, 969, 748, 693 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{52}\text{H}_{40}\text{N}_4$ [M^+] 720.3248, found 720.3252.

(*E,E,E*)-2,4,6-Tris(4-methoxystyryl)pyrimidine (2e). Synthesized from **1b** (100 mg, 0.42 mmol) and 4-methoxybenzaldehyde (114 mg, 0.83 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by recrystallization from $\text{CH}_2\text{Cl}_2/n$ -heptane. Yield: 156 mg (79 %); yellowish solid. R_f : 0.4 (SiO_2 ; petroleum ether:EtOAc, 8:2). Mp: 183 °C. ^1H NMR (300 MHz, CDCl_3): δ = 3.85 (s, 9H), 6.93–7.00 (m, 8H), 7.08 (s, 1H), 7.18 (d, 3J = 15.9 Hz, 1H), 7.57–7.65 (m, 6H), 7.88 (d, 3J = 15.9 Hz, 2H), 8.06 (d, 3J = 15.9 Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): δ = 55.46, 55.49, 112.8, 114.34, 114.4, 124.5, 126.3, 129.0, 129.2, 129.4, 136.1, 137.3, 160.4, 160.7, 163.1, 164.8 ppm All the atoms of carbon were not observed.. IR (ATR): ν = 2933, 1602, 1559, 1506, 1245, 1169, 1028, 959, 868, 810, 767 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{31}\text{H}_{28}\text{N}_2\text{O}_3$ [M^+] 476.2094, found 476.2094.

(*E,E,E*)-2-(4-Methoxystyryl)-4,6-bis(4-dimethylaminostyryl)pyrimidine (2f). Synthesized from **1b** (100 mg, 0.42 mmol) and 4-*N,N*-dimethylaminobenzaldehyde (125 mg, 0.83 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by recrystallization from $\text{CH}_2\text{Cl}_2/n$ -heptane. Yield: 154 mg (74 %); red solid. R_f : 0.3 (SiO_2 ; petroleum ether:EtOAc, 8:2). T_d : 250 °C. ^1H NMR (300 MHz, CDCl_3): δ = 3.03 (s, 12H), 3.85 (s, 3H), 6.71–6.74 (m, 4H), 6.88–6.95 (m, 4H), 7.07 (s, 1H), 7.17 (d, 3J = 15.9 Hz, 1H), 7.52–7.55 (m, 4H), 7.62–7.65 (m, 2H), 7.84 (d, 3J = 15.9 Hz, 2H), 8.05 (d, 3J = 15.9 Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): δ = 40.4, 55.4, 112.1, 112.2, 114.3, 122.0, 124.3, 126.6, 129.1, 129.6, 136.6, 136.8, 151.1, 160.2, 163.3, 164.7 ppm All the atoms of carbon were not observed.. IR (ATR): ν = 2924, 1600, 1550, 1497, 1355, 1244, 1142, 971, 806 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{33}\text{H}_{34}\text{N}_4\text{O}$ [M^+] 502.2727, found 502.2731.

(*E,E,E*)-2-(4-Methoxystyryl)-4,6-bis(4-diphenylaminostyryl)pyrimidine (2g). Synthesized from **1b** (100 mg, 0.42 mmol) and 4-*N,N*-diphenylaminobenzaldehyde (228 mg, 0.83 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by recrystallization from CH₂Cl₂/*n*-heptane. Yield: 225 mg (72 %); yellow solid. *R*_f: 0.7 (SiO₂; petroleum ether:EtOAc, 8:2). *T*_d: 270 °C. ¹H NMR (300 MHz, CDCl₃): δ = 3.85 (s, 3H), 6.92–7.21 (m, 24H), 7.27–7.32 (m, 6H), 7.48–7.50 (m, 4H), 7.61–7.64 (m, 2H), 7.86 (d, ³*J* = 15.9 Hz, 2H), 8.06 (d, ³*J* = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 55.5, 112.8, 114.3, 122.6, 123.7, 124.5, 125.2, 126.3, 128.7, 129.2, 129.4, 129.5, 129.7, 136.0, 137.2, 147.4, 149.0, 160.4, 163.0, 164.9 ppm. IR (ATR): ν = 3033, 1562, 1489, 1271, 1242, 1168, 972, 818, 749, 691 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₅₃H₄₂N₄O [M⁺] 750.3353, found 750.3361.

(*E,E,E*)-2-(4-Dimethylaminostyryl)-4,6-bis(4-methoxystyryl)pyrimidine (2h). Synthesized from **1c** (110 mg, 0.43 mmol) and 4-methoxybenzaldehyde (119 mg, 0.87 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by recrystallization from CH₂Cl₂/*n*-heptane. Yield: 121 mg (57 %); brown solid. *R*_f: 0.3 (SiO₂; petroleum ether:EtOAc, 8:2). Mp: 200 °C. ¹H NMR (300 MHz, CDCl₃): δ = 3.02 (s, 6H), 3.85 (s, 6H), 6.72–6.75 (m, 2H), 6.93–7.00 (m, 6H), 7.05 (s, 1H), 7.12 (d, ³*J* = 15.9 Hz, 1H), 7.57–7.61 (m, 6H), 7.87 (d, ³*J* = 15.9 Hz, 2H), 8.05 (d, ³*J* = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 40.4, 55.5, 112.2, 112.4, 114.4, 123.7, 124.7, 124.8, 129.0, 129.2, 135.9, 138.1, 151.0, 160.6, 163.0, 165.4 ppm. All the atoms of carbon were not observed. IR (ATR): ν = 2924, 1603, 1558, 1502, 1357, 1249, 1168, 1028, 961, 810 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₃₂H₃₁N₃O₂ [M⁺] 489.2411, found 489.2414.

(*E,E,E*)-2,4,6-Tris(4-dimethylaminostyryl)pyrimidine (2i). Synthesized from **1c** (244 mg, 0.96 mmol) and 4-*N,N*-dimethylaminobenzaldehyde (287 mg, 1.92 mmol) following the

general procedure for Knoevenagel condensation. The crude product was purified by recrystallization from CH₂Cl₂/*n*-heptane. Yield: 212 mg (43 %); brown solid. *R*_f: 0.1 (SiO₂; petroleum ether:EtOAc, 8:2). *T*_d: 250 °C. ¹H NMR (300 MHz, CDCl₃): δ = 3.02–3.03 (m, 18H), 6.71–6.75 (m, 6H), 6.91 (d, ³*J* = 15.9 Hz, 2H), 7.05 (s, 1H), 7.11 (d, ³*J* = 15.6 Hz, 1H), 7.53–7.61 (m, 6H), 7.83 (d, ³*J* = 15.9 Hz, 2H), 8.03 (d, ³*J* = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 40.4, 40.5, 111.6, 112.3, 122.3, 124.2, 124.4, 125.0, 129.1, 136.4, 137.6, 150.9, 151.1, 163.2, 165.2 ppm All the atoms of carbon were not observed. IR (ATR): ν = 2888, 1599, 1502, 1356, 1167, 965, 797 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₃₄H₃₇N₅ [M⁺] 515.3044, found 515.3044.

(*E,E,E*)-2-(4-Dimethylaminostyryl)-4,6-bis(4-diphenylaminostyryl)pyrimidine (2j).

Synthesized from **1c** (110 mg, 0.43 mmol) and 4-*N,N*-diphenylaminobenzaldehyde (238 mg, 0.87 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by recrystallization from CH₂Cl₂/*n*-heptane. Yield: 225 mg (68 %); yellow solid. *R*_f: 0.6 (SiO₂; petroleum ether:EtOAc, 8:2). *T*_d: 240 °C. ¹H NMR (300 MHz, CDCl₃): δ = 3.02 (s, 6H), 6.72–6.75 (m, 2H), 6.99 (d, ³*J* = 15.9 Hz, 2H), 7.05–7.16 (m, 18H), 7.27–7.32 (m, 8H), 7.48–7.50 (m, 4H), 7.57–7.60 (m, 2H), 7.85 (d, ³*J* = 15.9 Hz, 2H), 8.04 (d, ³*J* = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 40.4, 112.2, 112.3, 122.6, 123.7, 124.76, 124.78, 125.2, 128.7, 129.2, 129.5, 129.8, 135.8, 138.0, 147.4, 148.9, 151.0, 163.0, 165.4 ppm All the atoms of carbon were not observed. IR (ATR): ν = 3034, 1564, 1490, 1361, 1273, 1167, 971, 810, 749, 692 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₅₄H₄₅N₅ [M⁺] 763.3670, found 763.3673.

(*E,E,E*)-2-(4-Diphenylaminostyryl)-4,6-bis(4-methoxystyryl)pyrimidine (2k). Synthesized from **1d** (70 mg, 0.19 mmol) and 4-methoxybenzaldehyde (51 mg, 0.37 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by column chromatography (SiO₂, petroleum ether:EtOAc, 8:2). Yield: 83 mg (73 %); yellow solid. *R*_f:

0.5 (SiO₂; petroleum ether:EtOAc, 8:2). *T*_d: 310 °C. ¹H NMR (300 MHz, CDCl₃): δ = 3.86 (s, 6H), 6.93–7.20 (m, 16H), 7.27–7.32 (m, 4H), 7.53–7.60 (m, 6H), 7.87 (d, ³*J* = 15.9 Hz, 2H), 8.05 (d, ³*J* = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 55.5, 112.8, 114.4, 122.8, 123.6, 124.5, 126.4, 128.8, 128.9, 129.2, 129.5, 130.3, 136.1, 137.2, 147.5, 148.6, 160.7, 163.1, 164.9 ppm. IR (ATR): ν = 3033, 1562, 1506, 1279, 1248, 1031, 972, 808, 752, 695 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₄₂H₃₅N₃O₂ [M⁺] 613.2724, found 613.2728.

(*E,E,E*)-2-(4-Diphenylaminostyryl)-4,6-bis(4-dimethylaminostyryl)pyrimidine (2l).

Synthesized from **1d** (70 mg, 0.19 mmol) and 4-*N,N*-dimethylaminobenzaldehyde (56 mg, 0.37 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by column chromatography (SiO₂, petroleum ether:EtOAc, 8:2) and then by recrystallization from CH₂Cl₂/*n*-heptane. Yield: 62 mg (52 %); yellow solid. *R*_f: 0.5 (SiO₂; petroleum ether:EtOAc, 8:2). *T*_d: 195 °C. ¹H NMR (300 MHz, CDCl₃): δ = 3.03 (s, 12H), 6.71–6.74 (m, 4H), 6.90 (d, ³*J* = 15.9 Hz, 2H), 7.03–7.08 (m, 5H), 7.13–7.19 (m, 5H), 7.28–7.31 (m, 4H), 7.52–7.55 (m, 6H), 7.83 (d, ³*J* = 15.9 Hz, 2H), 8.03 (d, ³*J* = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 40.4, 112.0, 112.2, 122.1, 122.9, 123.5, 124.3, 125.1, 126.8, 128.7, 129.2, 129.5, 130.5, 136.6, 136.8, 147.5, 148.4, 151.2, 163.3, 164.7 ppm. IR (ATR): ν = 2853, 1602, 1553, 1492, 1358, 1276, 974, 808, 751, 696 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₄₄H₄₁N₅ [M⁺] 639.3357, found 639.3359.

(*E,E,E*)-2,4,6-Tris(4-diphenylaminostyryl)pyrimidine (2m). Synthesized from **1d** (33 mg, 0.09 mmol) and 4-*N,N*-diphenylaminobenzaldehyde (48 mg, 0.17 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by recrystallization from CH₂Cl₂/*n*-heptane. Yield: 44 mg (57 %); yellow solid. *R*_f: 0.8 (SiO₂; petroleum ether:EtOAc, 8:2). *T*_d: 310 °C. ¹H NMR (300 MHz, CDCl₃): δ = 6.97 (d, ³*J* = 15.9 Hz, 2H), 7.04–7.20 (m, 26H), 7.27–7.32 (m, 12H), 7.47–7.55 (m, 6H), 7.85 (d, ³*J* = 15.9 Hz, 2H), 8.04 (d, ³*J* = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 112.7, 122.6, 122.8,

123.5, 123.7, 124.3, 124.6, 125.1, 125.2, 126.4, 128.7, 129.49, 129.54, 129.6, 130.3, 136.0, 137.2, 147.3, 147.5, 148.6, 148.9, 163.0, 164.9 ppm. IR (ATR): ν = 3034, 1588, 1558, 1489, 1273, 1174, 970, 750, 693 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{64}\text{H}_{49}\text{N}_5$ [M^+] 887.3983, found 887.3982.

(*E,E,E*)-2-[(6-Methoxynaphthalen-2-yl)ethenyl]-4,6-bis(4-methoxystyryl)pyrimidine (2n).

Synthesized from **1e** (56 mg, 0.19 mmol) and 4-methoxybenzaldehyde (52 mg, 0.38 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by recrystallization from $\text{CH}_2\text{Cl}_2/n$ -heptane. Yield: 77 mg (77 %); yellowish solid. R_f : 0.3 (SiO_2 ; petroleum ether:EtOAc, 8:2). T_d : 290 $^\circ\text{C}$. ^1H NMR (300 MHz, CDCl_3): δ = 3.86 (s, 6H), 3.94 (s, 3H), 6.94–7.19 (m, 9H), 7.38 (d, 3J = 15.9 Hz, 1H), 7.59–7.61 (m, 4H), 7.74–7.98 (m, 6H), 8.24 (d, 3J = 15.9 Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): δ = 55.5, 106.1, 113.1, 114.5, 119.2, 124.5, 124.8, 127.4, 127.8, 128.6, 128.9, 129.1, 129.2, 130.0, 132.1, 135.1, 136.2, 137.9, 158.4, 160.7, 163.1, 164.7 ppm. IR (ATR): ν = 2935, 1601, 1559, 1505, 1366, 1246, 1169, 1027, 959, 838, 809 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{35}\text{H}_{30}\text{N}_2\text{O}_3$ [M^+] 526.2251, found 526.2252.

(*E,E,E*)-2-[(6-Methoxynaphthalen-2-yl)ethenyl]-4,6-bis(4-

dimethylaminostyryl)pyrimidine (2o). Synthesized from **1e** (53 mg, 0.18 mmol) and 4-*N,N*-dimethylaminobenzaldehyde (54 mg, 0.36 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by recrystallization from $\text{CH}_2\text{Cl}_2/n$ -heptane. Yield: 70 mg (70 %); orange solid. R_f : 0.2 (SiO_2 ; petroleum ether:EtOAc, 8:2). T_d : 250 $^\circ\text{C}$. ^1H NMR (300 MHz, CDCl_3): δ = 3.03 (s, 12H), 3.94 (s, 3H), 6.72–6.75 (m, 4H), 6.92 (d, 3J = 15.9 Hz, 2H), 7.07–7.18 (m, 3H), 7.38 (d, 3J = 15.9 Hz, 1H), 7.54–7.57 (m, 4H), 7.74–7.90 (m, 5H), 7.99 (s, 1H), 8.23 (d, 3J = 15.9 Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): δ = 40.4, 55.5, 106.1, 112.2, 112.3, 119.1, 122.0, 124.3, 124.8, 127.3, 128.2, 128.4, 129.2, 130.0, 132.2, 135.0, 136.7, 137.4, 151.2, 158.3, 163.4, 164.5 ppm. All the atoms of

carbon were not observed. IR (ATR): $\nu = 2853, 1600, 1552, 1357, 1144, 969, 851, 804 \text{ cm}^{-1}$. HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{37}\text{H}_{36}\text{N}_4\text{O} [\text{M}^+]$ 552.2884, found 552.2889.

(*E,E,E*)-2-[(6-Methoxynaphthalen-2-yl)ethenyl]-4,6-bis(4-diphenylaminostyryl)pyrimidine (2p). Synthesized from **1e** (37 mg, 0.12 mmol) and 4-*N,N*-diphenylaminobenzaldehyde (69 mg, 0.25 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by recrystallization from $\text{CH}_2\text{Cl}_2/n$ -heptane. Yield: 30 mg (30 %); orange solid. R_f : 0.6 (SiO_2 ; petroleum ether:EtOAc, 8:2). T_d : 220 °C. ^1H NMR (300 MHz, CDCl_3): $\delta = 3.94$ (s, 3H), 6.97–7.17 (m, 22H), 7.28–7.40 (m, 8H), 7.49–7.52 (m, 4H), 7.74–7.79 (m, 2H), 7.84–7.92 (m, 3H), 7.98 (s, 1H), 8.23 (d, $^3J = 15.9 \text{ Hz}$, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): $\delta = 55.5, 106.1, 113.0, 119.2, 122.6, 123.8, 124.5, 124.8, 125.2, 127.4, 127.8, 128.6, 128.8, 129.1, 129.5, 129.6, 130.0, 132.1, 135.1, 136.1, 137.8, 147.4, 149.0, 158.4, 163.1, 164.8$ ppm. IR (ATR): $\nu = 3034, 1588, 1558, 1490, 1268, 1174, 969, 849, 751, 694 \text{ cm}^{-1}$. HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{57}\text{H}_{44}\text{N}_4\text{O} [\text{M}^+]$ 800.3510, found 800.3518.

(*E,E,E*)-2-(4-Trifluoromethylstyryl)-4,6-bis(4-methoxystyryl)pyrimidine (2q). Synthesized from **1f** (90 mg, 0.32 mmol) and 4-methoxybenzaldehyde (88 mg, 0.65 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by column chromatography (SiO_2 , petroleum ether:EtOAc, 7:3). Yield: 71 mg (43 %); yellowish solid. R_f : 0.7 (SiO_2 ; petroleum ether:EtOAc, 7:3). T_d : 280 °C. ^1H NMR (300 MHz, CDCl_3): $\delta = 3.86$ (s, 6H), 6.94–7.02 (m, 6H), 7.13 (s, 1H), 7.38 (d, $^3J = 15.9 \text{ Hz}$, 1H), 7.58–7.61 (m, 4H), 7.65–7.68 (m, 2H), 7.76–7.79 (m, 2H), 7.91 (d, $^3J = 15.9 \text{ Hz}$, 2H), 8.11 (d, $^3J = 15.9 \text{ Hz}$, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): $\delta = 55.5, 113.6, 114.5, 124.2, 124.3$ (q, $^1J_{\text{CF}} = 270 \text{ Hz}$), 125.8 (q, $^3J_{\text{CF}} = 4 \text{ Hz}$), 127.8, 128.8, 129.3, 130.4 (q, $^2J_{\text{CF}} = 32 \text{ Hz}$), 131.1, 135.8, 136.5, 140.1, 160.8, 163.2, 163.9 ppm. IR (ATR): $\nu = 2838, 1568, 1325, 1251, 1107,$

976, 818 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{31}\text{H}_{25}\text{F}_3\text{N}_2\text{O}_2$ [M^+] 514.1863, found 514.1861.

(*E,E,E*)-2-(4-Trifluoromethylstyryl)-4,6-bis(4-dimethylaminostyryl)pyrimidine (2r).

Synthesized from **1f** (90 mg, 0.32 mmol) and 4-*N,N*-dimethylaminobenzaldehyde (97 mg, 0.65 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by column chromatography (SiO_2 , petroleum ether:EtOAc, 8:2). Yield: 69 mg (40 %); orange solid. R_f : 0.3 (SiO_2 ; petroleum ether:EtOAc, 8:2). Mp: 210 $^\circ\text{C}$. ^1H NMR (300 MHz, CDCl_3): δ = 3.04 (s, 12H), 6.72–6.75 (m, 4H), 6.91 (d, 3J = 15.9 Hz, 2H), 7.10 (s, 1H), 7.37 (d, 3J = 15.9 Hz, 1H), 7.53–7.56 (m, 4H), 7.64–7.67 (m, 2H), 7.76–7.79 (m, 2H), 7.86 (d, 3J = 15.9 Hz, 2H), 8.09 (d, 3J = 15.9 Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): δ = 40.4, 112.2, 112.9, 121.7, 124.1, 124.3 (q, $^1J_{\text{CF}}$ = 270 Hz), 125.8 (q, $^3J_{\text{CF}}$ = 4 Hz), 127.8, 129.2, 130.2 (q, $^2J_{\text{CF}}$ = 32 Hz), 131.4, 135.4, 137.0, 140.2, 151.2, 163.5, 163.8 ppm. IR (ATR): ν = 2892, 1494, 1318, 1116, 1065, 974, 809 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{33}\text{H}_{31}\text{F}_3\text{N}_4$ [M^+] 540.2495, found 540.2501.

(*E,E,E*)-2-(4-Trifluoromethylstyryl)-4,6-bis(4-diphenylaminostyryl)pyrimidine (2s).

Synthesized from **1f** (90 mg, 0.32 mmol) and 4-*N,N*-diphenylaminobenzaldehyde (177 mg, 0.65 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by column chromatography (SiO_2 , petroleum ether:EtOAc, 9:1). Yield: 70 mg (28 %); yellow solid. R_f : 0.7 (SiO_2 ; petroleum ether:EtOAc, 9:1). T_d : 300 $^\circ\text{C}$. ^1H NMR (300 MHz, CDCl_3): δ = 7.00 (d, 3J = 15.9 Hz, 2H), 7.08–7.19 (m, 18H), 7.30–7.43 (m, 8H), 7.50–7.53 (m, 4H), 7.66–7.69 (m, 2H), 7.78–7.80 (m, 2H), 7.90 (d, 3J = 15.9 Hz, 2H), 8.12 (d, 3J = 15.9 Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): δ = 113.6, 123.8, 124.0, 124.1, 124.5 (q, $^1J_{\text{CF}}$ = 276 Hz), 125.3, 125.8 (q, $^3J_{\text{CF}}$ = 4 Hz), 127.8, 128.8, 129.4, 129.6, 130.4 (q, $^2J_{\text{CF}}$ = 32 Hz), 131.1, 135.7, 136.3, 140.0 (q, $^4J_{\text{CF}}$ = 1 Hz), 147.3, 149.1, 163.2, 163.9 ppm. IR (ATR): ν

= 3033, 1559, 1490, 1320, 1066, 968, 751 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{53}\text{H}_{39}\text{F}_3\text{N}_4$ [M^+] 788.3121, found 788.3111.

(E)-2-Chloro-4-(4-dimethylaminostyryl)-6-methylpyrimidine (3a). Synthesized from 4-ethynyl-*N,N*-dimethylaniline (250 mg, 1.72 mmol) and 2,4-dichloro-6-methylpyrimidine (179 mg, 1.1 mmol) following the general procedure for Suzuki-Miyaura reaction. The crude product was purified by column chromatography (SiO_2 , petroleum ether:EtOAc, 8:2). Yield: 156 mg (52 %); brown solid. R_f : 0.4 (SiO_2 ; petroleum ether:EtOAc, 8:2). Mp: 163.4–165.7 $^{\circ}\text{C}$. ^1H NMR (300 MHz, CDCl_3): δ = 2.49 (s, 3H), 3.03 (s, 6H), 6.68–6.78 (m, 3H), 6.99 (s, 1H), 7.47–7.50 (m, 2H), 7.83 (d, 3J = 15.9 Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): δ = 24.0, 40.3, 112.1, 115.6, 119.2, 123.3, 129.6, 139.5, 151.6, 161.1, 166.2, 169.9 ppm. IR (ATR): ν = 2913, 2193, 1566, 1258, 979, 809, 750, 765 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{15}\text{H}_{16}\text{ClN}_3$ [M^+] 273.1027, found 273.1023.

(E)-2-Chloro-4-(4-methoxystyryl)-6-methylpyrimidine (3b). Synthesized from 4-ethynylanisole (311 mg, 2.35 mmol) and 2,4-dichloro-6-methylpyrimidine (245 mg, 1.5 mmol) following the general procedure for Suzuki-Miyaura reaction. The crude product was purified by column chromatography (SiO_2 , petroleum ether:EtOAc, 7:3). Yield: 215 mg (55 %); yellowish solid. R_f : 0.4 (SiO_2 ; petroleum ether:EtOAc, 7:3). Mp: 78.9–81.8 $^{\circ}\text{C}$. ^1H NMR (300 MHz, CDCl_3): δ = 2.51 (s, 3H), 3.85 (s, 3H), 6.83 (d, 3J = 15.9 Hz, 1H), 6.90–6.95 (m, 2H), 7.04 (s, 1H), 7.51–7.56 (m, 2H), 7.86 (d, 3J = 15.9 Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): δ = 24.1, 55.5, 114.6, 116.2, 122.0, 128.2, 129.6, 138.7, 161.18, 161.21, 165.6, 170.5 ppm. IR (ATR): ν = 2924, 1570, 1512, 1256, 1178, 1020, 967, 819 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{14}\text{H}_{13}\text{ClN}_2\text{O}$ [M^+] 260.0711, found 260.0710.

(E,E)-2-(4-Methoxystyryl)-4-(4-dimethylaminostyryl)-6-methylpyrimidine (4a). Synthesized from 4-ethynylanisole (91 mg, 0.69 mmol) and **3a** (120 mg, 0.44 mmol) following the general procedure for Suzuki-Miyaura reaction. The crude product was purified

by column chromatography (SiO₂, petroleum ether:EtOAc, 7:3). Yield: 65 mg (40 %); orange solid. *R*_f: 0.3 (SiO₂; petroleum ether:EtOAc, 7:3). Mp: 79.9–81.5 °C. ¹H NMR (300 MHz, CDCl₃): δ = 2.51 (s, 3H), 3.02 (s, 6H), 3.84 (s, 3H), 6.70–6.73 (m, 2H), 6.83–6.94 (m, 4H), 7.13 (d, ³*J* = 15.9 Hz, 1H), 7.50–7.53 (m, 2H), 7.58–7.61 (m, 2H), 7.81 (d, ³*J* = 15.9 Hz, 1H), 7.99 (d, ³*J* = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 24.3, 40.4, 55.4, 112.2, 114.3, 114.4, 121.6, 124.1, 126.1, 129.1, 129.2, 129.4, 137.1, 151.2, 160.3, 163.2, 164.6, 166.7 ppm All the atoms of carbon were not observed. IR (ATR): ν = 2922, 1602, 1509, 1352, 1242, 1169, 973, 809 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₂₄H₂₅N₃O [M⁺] 371.1992, found 371.1988.

(*E,E*)-2-(4-Dimethylaminostyryl)-4-(4-methoxystyryl)-6-methylpyrimidine (4b).

Synthesized from 4-ethynyl-*N,N*-dimethylaniline (155 mg, 1.06 mmol) and **3b** (177 mg, 0.68 mmol) following the general procedure for Suzuki-Miyaura reaction. The crude product was purified by column chromatography (SiO₂, petroleum ether:EtOAc, 7:3). Yield: 190 mg (75 %); brown solid. *R*_f: 0.2 (SiO₂; petroleum ether:EtOAc, 7:3). Mp: 123.5–125.7 °C. ¹H NMR (300 MHz, CDCl₃): δ = 2.52 (s, 3H), 3.01 (s, 6H), 3.84 (s, 3H), 6.70–6.73 (m, 2H), 6.90–6.95 (m, 4H), 7.07 (d, ³*J* = 15.9 Hz, 1H), 7.54–7.58 (m, 4H), 7.83 (d, ³*J* = 15.9 Hz, 1H), 7.99 (d, ³*J* = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 24.4, 40.4, 55.5, 112.2, 114.3, 114.4, 123.3, 124.4, 124.6, 128.9, 129.1, 136.0, 138.1, 151.0, 160.6, 162.5, 165.2, 166.9 ppm All the atoms of carbon were not observed. IR (ATR): ν = 2918, 1599, 1509, 1351, 1249, 1162, 970, 808 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₂₄H₂₅N₃O [M⁺] 371.1992, found 371.1993.

(*E,E,E*)-2-(4-Methoxystyryl)-4-(4-dimethylaminostyryl)-6-(4-

diphenylaminostyryl)pyrimidine (5a). Synthesized from **4a** (45 mg, 0.12 mmol) and 4-*N,N*-diphenylaminobenzaldehyde (33 mg, 0.12 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by column chromatography

(SiO₂, petroleum ether:EtOAc, 8:2). Yield: 46 mg (61 %); orange solid. *R*_f: 0.5 (SiO₂; petroleum ether:EtOAc, 8:2). *T*_d: 240 °C. ¹H NMR (300 MHz, CDCl₃): δ = 3.03 (s, 6H), 3.85 (s, 3H), 6.71–6.74 (m, 2H), 6.88–7.20 (m, 14H), 7.27–7.32 (m, 4H), 7.48–7.55 (m, 4H), 7.62–7.65 (m, 2H), 7.85 (d, ³*J* = 15.9 Hz, 2H), 8.05 (d, ³*J* = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 40.4, 55.5, 112.2, 112.5, 114.3, 121.9, 122.6, 123.7, 124.2, 124.7, 125.2, 126.5, 128.7, 129.2, 129.2, 129.50, 129.54, 129.8, 135.7, 136.9, 137.0, 147.4, 148.9, 151.2, 160.3, 162.7, 163.6, 164.8 ppm. IR (ATR): ν = 2925, 1561, 1490, 1247, 1170, 1144, 971, 694 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₄₃H₃₈N₄O [M⁺] 626.3040, found 626.3038.

(*E,E,E*)-2-(4-Dimethylaminostyryl)-4-(4-methoxystyryl)-6-(4-diphenylaminostyryl)pyrimidine (5b). Synthesized from **4b** (150 mg, 0.40 mmol) and 4-*N,N*-diphenylaminobenzaldehyde (110 mg, 0.40 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by column chromatography (SiO₂, petroleum ether:EtOAc, 7:3). Yield: 84 mg (33 %); orange solid. *R*_f: 0.5 (SiO₂; petroleum ether:EtOAc, 7:3). *T*_d: 210 °C. ¹H NMR (300 MHz, CDCl₃): δ = 3.02 (s, 6H), 3.85 (s, 3H), 6.72–6.75 (m, 2H), 6.93–7.16 (m, 14H), 7.27–7.32 (m, 4H), 7.48–7.51 (m, 2H), 7.57–7.60 (m, 4H), 7.82–7.90 (m, 2H), 8.05 (d, ³*J* = 15.9 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 40.4, 55.5, 112.3, 112.3, 114.4, 122.6, 123.7, 124.2, 124.4, 124.7, 124.8, 125.2, 128.4, 128.7, 129.0, 129.2, 129.4, 129.5, 129.8, 135.9, 138.1, 147.4, 148.9, 151.0, 160.6, 162.9, 163.0, 165.4 ppm. IR (ATR): ν = 2921, 1500, 1359, 1248, 1166, 971, 809, 693 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₄₃H₃₈N₄O [M⁺] 626.3040, found 626.3058.

(*E*)-2-Styryl-4-methylpyrimidine (6a). Synthesized from phenylacetylene (176 mg, 1.72 mmol) and 2-chloro-4-methylpyrimidine (142 mg, 1.1 mmol) following the general procedure for Suzuki-Miyaura reaction. The crude product was purified by column chromatography (SiO₂, petroleum ether:EtOAc, 8:2). Yield: 70 mg (32 %); white solid. *R*_f: 0.4 (SiO₂; petroleum ether:EtOAc, 8:2). Mp: 67.2–69.9 °C (lit.³² 65–67°C). ¹H NMR (300 MHz, CDCl₃):

δ = 2.54 (s, 3H), 6.97 (d, 3J = 4.8 Hz, 1H), 7.22 (d, 3J = 15.9 Hz, 1H), 7.30–7.41 (m, 3H), 7.61–7.63 (m, 2H), 7.98 (d, 3J = 15.9 Hz, 1H), 8.56 (d, 3J = 4.8 Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): δ = 24.4, 118.3, 127.7, 128.9, 129.1, 136.3, 137.9, 156.8, 164.7, 167.1 ppm. All the atoms of carbon were not observed. IR (ATR): ν = 2918, 1547, 1440, 1385, 978, 790, 747 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{13}\text{H}_{13}\text{N}_2$ $[(\text{M}+\text{H})^+]$ 197.1073, found 197.1073.

(*E*)-2-(4-Methoxystyryl)-4-methylpyrimidine (6b).

Synthesized from 4-ethynylanisole (311 mg, 2.35 mmol) and 2-chloro-4-methylpyrimidine (193 mg, 1.50 mmol) following the general procedure for Suzuki-Miyaura reaction. The crude product was purified by column chromatography (SiO_2 , petroleum ether:EtOAc, 7:3). Yield: 206 mg (61 %); brownish solid. R_f : 0.2 (SiO_2 ; petroleum ether:EtOAc, 7:3). Mp: 102.3–104.9 $^{\circ}\text{C}$. ^1H NMR (300 MHz, CDCl_3): δ = 2.53 (s, 3H), 3.83 (s, 3H), 6.90–6.95 (m, 3H), 7.09 (d, 3J = 15.9 Hz, 1H), 7.55–7.58 (m, 2H), 7.93 (d, 3J = 15.9 Hz, 1H), 8.54 (d, 3J = 5.1 Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): δ = 24.4, 55.5, 114.4, 117.9, 125.5, 129.1, 129.2, 137.6, 156.7, 160.6, 165.0, 167.1 ppm. IR (ATR): ν = 2937, 1566, 1509, 1249, 1178, 1028, 981, 821, 775 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{14}\text{H}_{14}\text{N}_2\text{O}$ $[\text{M}^+]$ 226.1101, found 226.1100.

(*E*)-2-(4-Dimethylaminostyryl)-4-methylpyrimidine (6c).

Synthesized from 4-ethynyl-*N,N*-dimethylaniline (250 mg, 1.72 mmol) and 2-chloro-4-methylpyrimidine (142 mg, 1.1 mmol) following the general procedure for Suzuki-Miyaura reaction. The crude product was purified by column chromatography (SiO_2 , petroleum ether:EtOAc, 8:2). Yield: 85 mg (32 %); brown solid. R_f : 0.3 (SiO_2 ; petroleum ether:EtOAc, 8:2). Mp: 117.3–119.8 $^{\circ}\text{C}$. ^1H NMR (300 MHz, CDCl_3): δ = 2.51 (s, 3H), 2.99 (s, 6H), 6.68–6.71 (m, 2H), 6.89 (d, 3J = 5.1 Hz, 1H), 7.02 (d, 3J = 15.9 Hz, 1H), 7.49–7.52 (m, 2H), 7.92 (d, 3J = 15.9 Hz, 1H), 8.50 (d, 3J = 5.1 Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): δ = 24.3,

40.3, 112.2, 117.3, 122.6, 124.3, 129.2, 138.5, 151.1, 156.5, 165.3, 166.9 ppm. IR (ATR): ν = 2912, 1602, 1523, 1435, 1363, 1167, 987, 805, 768, 750 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{15}\text{H}_{17}\text{N}_3$ [M^+] 239.1417, found 239.1415.

(E)-2-(4-Diphenylaminostyryl)-4-methylpyrimidine (6d). Synthesized from 4-ethynyl-*N,N*-diphenylaniline (275 mg, 1.02 mmol) and 2-chloro-4-methylpyrimidine (84 mg, 0.65 mmol) following the general procedure for Suzuki-Miyaura reaction. The crude product was purified by column chromatography (SiO_2 , petroleum ether:EtOAc, 8:2). Yield: 102 mg (43 %); yellow solid. R_f : 0.2 (SiO_2 ; petroleum ether:EtOAc, 8:2). Mp: 120.9–123.5 °C. ^1H NMR (300 MHz, CDCl_3): δ = 2.53 (s, 3H), 6.94 (d, 3J = 5.1 Hz, 1H), 7.02–7.15 (m, 10H), 7.25–7.31 (m, 3H), 7.46–7.49 (m, 2H), 7.92 (d, 3J = 15.9 Hz, 1H), 8.54 (d, 3J = 5.1 Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): δ = 24.4, 117.9, 122.6, 123.6, 125.2, 125.4, 128.7, 129.5, 129.8, 137.6, 147.4, 148.8, 156.7, 165.0, 167.1 ppm. IR (ATR): ν = 3036, 1572, 1487, 1266, 984, 831, 750, 695 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{25}\text{H}_{21}\text{N}_3$ [M^+] 363.1730, found 363.1723.

(E,E)-2,4-Distyrylpyrimidine (7a). Synthesized from **6a** (50 mg, 0.25 mmol) and benzaldehyde (28 mg, 0.25 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by column chromatography (SiO_2 ; petroleum ether:EtOAc, 8:2). Yield: 41 mg (57 %); white solid. R_f : 0.4 (SiO_2 ; petroleum ether:EtOAc, 8:2). Mp: 137 °C. ^1H NMR (300 MHz, CDCl_3): δ = 7.08–7.15 (m, 2H), 7.32–7.41 (m, 7H), 7.63–7.68 (m, 4H), 7.92 (d, 3J = 15.9 Hz, 1H), 8.05 (d, 3J = 15.9 Hz, 1H), 8.67 (d, 3J = 5.1 Hz, 1H) ppm. ^{13}C NMR (75 MHz, CDCl_3): δ = 115.9, 126.3, 127.8, 128.0, 128.9, 129.0, 129.1, 129.5, 135.9, 136.3, 137.2, 138.1, 157.6, 162.5, 164.9 ppm. All the atoms of carbon were not observed. IR (ATR): ν = 3054, 3026, 1637, 1558, 1537, 1388, 975, 876, 738, 688 cm^{-1} . HR-MALDI-MS (DCTB): m/z calculated for $\text{C}_{20}\text{H}_{17}\text{N}_2$ [$(\text{M}+\text{H})^+$] 285.1386, found 285.1385.

(*E,E*)-2,4-Bis(4-methoxystyryl)pyrimidine (7b). Synthesized from **6b** (170 mg, 0.75 mmol) and 4-methoxybenzaldehyde (103 mg, 0.75 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by recrystallization from CH₂Cl₂/*n*-heptane. Yield: 218 mg (84 %); silver solid. *R*_f: 0.1 (SiO₂; petroleum ether:EtOAc, 7:3). Mp: 185 °C. ¹H NMR (300 MHz, CDCl₃): δ = 3.85 (s, 6H), 6.92–6.98 (m, 5H), 7.07 (d, ³*J* = 5.1 Hz, 1H), 7.14 (d, ³*J* = 15.9 Hz, 1H), 7.56–7.62 (m, 4H), 7.85 (d, ³*J* = 15.9 Hz, 1H), 7.99 (d, ³*J* = 15.9 Hz, 1H), 8.60 (d, ³*J* = 5.1 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 55.47, 55.49, 114.4, 114.5, 115.3, 124.1, 125.8, 128.7, 129.1, 129.2, 129.3, 136.7, 137.5, 157.3, 160.5, 160.8, 162.8, 165.1 ppm. IR (ATR): ν = 2964, 1560, 1250, 1177, 1028, 972, 826 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₂₂H₂₁N₂O₂ [(*M*+H)⁺] 345.1598, found 345.1592.

(*E,E*)-2,4-Bis(4-dimethylaminostyryl)pyrimidine (7c). Synthesized from **6c** (41 mg, 0.17 mmol) and 4-*N,N*-dimethylaminobenzaldehyde (26 mg, 0.17 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by recrystallization from CH₂Cl₂/*n*-heptane. Yield: 55 mg (85 %); brown solid. *R*_f: 0.2 (SiO₂; petroleum ether:EtOAc, 8:2). Mp: 243 °C. ¹H NMR (300 MHz, CDCl₃): δ = 3.02–3.03 (m, 12H), 6.70–6.74 (m, 4H), 6.88 (d, ³*J* = 15.9 Hz, 1H), 7.01–7.09 (m, 2H), 7.51–7.57 (m, 4H), 7.80 (d, ³*J* = 15.9 Hz, 1H), 7.96 (d, ³*J* = 15.9 Hz, 1H), 8.54 (d, ³*J* = 5.1 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 40.4, 40.5, 112.2, 112.3, 114.3, 121.7, 123.4, 124.1, 124.6, 129.2, 129.3, 137.3, 138.0, 151.1, 151.3, 156.9, 163.3, 165.5 ppm. IR (ATR): ν = 2920, 1602, 1550, 1520, 1359, 1163, 970, 810, 781 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₂₄H₂₆N₄ [*M*⁺] 370.2152, found 370.2150.

(*E,E*)-2,4-Bis(4-diphenylaminostyryl)pyrimidine (7d). Synthesized from **6d** (76 mg, 0.21 mmol) and 4-*N,N*-diphenylaminobenzaldehyde (58 mg, 0.21 mmol) following the general procedure for Knoevenagel condensation. The crude product was purified by recrystallization

from CH₂Cl₂/*n*-heptane. Yield: 51 mg (39 %); yellow solid. *R*_f: 0.3 (SiO₂; petroleum ether:EtOAc, 8:2). *T*_d: 250 °C. ¹H NMR (300 MHz, CDCl₃): δ = 6.92–6.97 (m, 2H), 7.04–7.15 (m, 19H), 7.29–7.32 (m, 6H), 7.46–7.52 (m, 4H), 7.82 (d, ³*J* = 15.9 Hz, 1H), 7.97 (d, ³*J* = 15.9 Hz, 1H), 8.59 (d, ³*J* = 5.4 Hz, 1H) ppm. ¹³C NMR (75 MHz, CDCl₃): δ = 115.1, 122.5, 122.7, 123.6, 123.8, 124.1, 125.2, 125.3, 125.9, 128.78, 128.82, 129.3, 129.5, 129.6, 130.0, 136.7, 137.5, 147.3, 147.4, 148.8, 149.1, 157.2, 162.9, 165.1 ppm. IR (ATR): ν = 3034, 2924, 1588, 1556, 1490, 1274, 1174, 972, 831, 751, 693 cm⁻¹. HR-MALDI-MS (DCTB): *m/z* calculated for C₄₄H₃₄N₄ [M⁺] 618.2778, found 618.2779.

Associated contents

The supporting information is available free of charge on the ACS Publications website at doi:

Experimental and calculated absorption spectra in dichloromethane as well as correlation between experimental and emission maxima for **A3**, **2g**, **2j**, **2m**, **2k**, cartesian coordinates, total energies for **A3**, **2g**, **2j**, **2m**, **2k** emission maxima (*λ_{em}*) vs *E_T* (30) for compounds **2b-g**, **2i-s**, **5a-b**, **7c-d**, DSC curves of chromophores **2**, **5**, **7**, **A2** and **A3**, ¹H and ¹³C NMR spectra for compounds **1-7**, ORTEP drawing of the chromophore **2h** with thermal ellipsoid at 50% (pdf).

X-ray crystallographic data of compound **2h** (CIF)

Conflicts of interest

There are no conflict to declare.

Acknowledgements

M. F. thanks the Région Bretagne, France for funding.

References

- 1 (a) Achelle, S.; Rodríguez-López, J.; Robin-le Guen, F. Photoluminescence Properties of
2 Aryl-, Arylvinyl-, and Arylethynylpyrimidine Derivatives. *Chem. Select* **2018**, 3, 1852-1886;
3
4
5
6
7
8 (b) Achelle, S. Plé, N. Pyrimidine Ring as Building Block for the Synthesis of Functionalized
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
- 1 (a) Achelle, S.; Rodríguez-López, J.; Robin-le Guen, F. Photoluminescence Properties of Aryl-, Arylvinyl-, and Arylethynylpyrimidine Derivatives. *Chem. Select* **2018**, 3, 1852-1886;
(b) Achelle, S. Plé, N. Pyrimidine Ring as Building Block for the Synthesis of Functionalized Π -Conjugated Materials. *Curr. Org. Synth.* **2013**, 9, 163-187.
- 2 (a) Nakao, K.; Sasabe, H.; Komatsu, R.; Hayasaka, Y.; Ohsawa, T.; Kido, J. Unlocking the Potential of Pyrimidine Conjugate Emitters to Realize High-Performance Organic Light-Emitting Devices. *Adv. Opt. Mater.* **2017**, 5, 1600843; (b) Komatsu, R.; Sasabe, H.; Seino, Y.; Nakao, K.; Kido, J. Light-Blue Thermally Activated Delayed Fluorescent Emitters Realizing a High External Quantum Efficiency of 25% and Unprecedented Low Drive Voltages in OLEDs. *J. Mater. Chem. C* **2016**, 4, 2274-2278; (c) Wu, K.; Zhang, T.; Zhan, L.; Zhong, C.; Gong, S.; Jiang, N.; Lu, Z.-H.; Yang, C. Optimizing Optoelectronic Properties of Pyrimidine-Based TADF Emitters by Changing the Substituent for Organic Light-Emitting Diodes with External Quantum Efficiency Close to 25% and Slow Efficiency Roll-Off. *Chem. Eur. J.* **2016**, 22, 10860-10866; (d) Komatsu, R.; Ohsawa, T.; Sasabe, H.; Nakao, K.; Hayasaka, Y.; Kido, J. Manipulating the Electronic Excited State Energies of Pyrimidine-Based Thermally Activated Delayed Fluorescence Emitters To Realize Efficient Deep-Blue Emission. *ACS Appl. Mater. Interfaces* **2017**, 9, 4742-4749; (e) R. Komatsu, H. Sasabe, J. Kido, *J. Photon. Energy* **2018**, 8, 032108.
- 3 (a) Li, L.; Ge, J.; Wu, H.; Xu, Q.-H.; Yao, S. Q. Organelle-Specific Detection of Phosphatase Activities with Two-Photon Fluorogenic Probes in Cells and Tissues. *J. Am. Chem. Soc.* **2012**, 134, 12157-12167; (b) Na, Z.; Li, L.; Uttamchandani, M.; Yao, S. Q. Microarray-Guided Discovery of Two-Photon (2P) Small Molecule Probes For Live-Cell Imaging of Cysteiny Cathepsin Activities. *Chem. Commun.* **2012**, 48, 7304-7306; (c) Zhang,

Q.; Tian, X.; Hu, Z.; Brommesson, C.; Wu, J.; Zhou, H.; Yang, J.; Sun, Z.; Tian, Y.; Uvdal, K. Nonlinear Optical Response and Two-Photon Biological Applications of a New Family of Imidazole-Pyrimidine Derivatives. *Dyes Pigm.* **2016**, *126*, 286-295; (d) Liu, B.; Zhang, H.-L.; Liu, J.; Zhao, Y.-D.; Luo, Q.-M.; Huang, Z.-L. Novel Pyrimidine-Based Amphiphilic Molecules: Synthesis, Spectroscopic Properties and Applications in Two-Photon Fluorescence Microscopic Imaging. *J. Mater. Chem.* **2007**, *17*, 2921-2929.

4 Malval, J.-P.; Achelle, S.; Bodiou, L.; Spangenberg, A.; Gomez, L. C.; Soppera, O.; Robin-le Guen, F. Two-Photon Absorption in a Conformationally Twisted D- π -A Oligomer: a Synergic Photosensitizing Approach For Muultiphoton Lithography. *J. Mater. Chem. C* **2014**, *2*, 7869-7880.

5 (a) Achelle, S.; Noura, I.; Pfaffinger, B.; Ramondenc, Y.; Plé, N.; Rodríguez-López, J. V-Shaped 4,6-Bis(arylvinyl)pyrimidine Oligomers: Synthesis and Optical Properties. *J. Org. Chem.* **2009**, *74*, 3711-3717; (b) Tang, R.; Wang, X.; Zhang, W.; Zhuang, X.; Bi, S.; Zhang, W.; Zhang, F. Aromatic Azaheterocycle-Cored Luminogens With Tunable Physical Properties via Nitrogen Atoms For Sensing Strong Acids. *J. Mater. Chem. C* **2016**, *4*, 7640-7648.

6 (a) Hadad, C.; Achelle, S.; López-Solera, I.; García-Martínez, J. C.; Rodríguez-López, J. Metal Cation Complexation Studies of 4-Arylvinyl-2,6-di(pyridin-2-yl)pyrimidines: Effect on the Optical Properties. *Dyes Pigm.* **2013**, *97*, 230-237; (b) Weng, J.; Mei, Q.; Ling, Q.; Fan, Q.; Huang, W. A New Colorimetric and Fluorescent Ratiometric Sensor for Hg²⁺ Based on 4-Pyren-1-yl-pyrimidine. *Tetrahedron*, **2012**, *68*, 3129-3134.

7 (a) Verbitskiy, E. V. Baranova, A. A.; Lugovik, K. I.; Shafikov, M. Z.; Khokhlov, K. O.; EChepprakova, E. M.; Rusinov, G. L.; Chupakhin, O. N.; Charushin, V. N. Detection of Nitroaromatic Explosives by new D- π -A Sensing Fluorophores on the Basis of the Pyrimidine Scaffold. *Anal. Bioanal. Chem.* **2016**, *408*, 4093-4101; (b) Verbitskiy, E. V.; Baranova, A. A.;

- Lugovik, K. I.; Khokhlov, K. O.; Cheprakova, E. M.; Shafikov, M. Z.; Rusinov, G. L.; Chupakhin, O. N.; Charushin, V. N. New 4,5-Di(hetero)arylpurimidines as Sensing Elements for Detection of Nitroaromatic Explosives in Vapor Phase. *Dyes Pigm.* **2017**, *137*, 360-371.
- 8 Boländer, A.; Kiesser, D.; Voss, C.; Bauer, S.; Schön, C.; Burgold, S.; Bittner, T.; Hölzer, J.; Heyny-von Haußen, R.; Mall, G.; Goetschy, V.; Czech, C.; Knust, H.; Berger, R.; Herms, J.; Hilger, I.; Schmidt, B. Bis(arylvinyl)pyrazines, -purimidines, and -pyridazines As Imaging Agents for Tau Fibril and β -Amyloid Plaques in Alzheimer's Disease Models. *J. Med. Chem.* **2012**, *55*, 9170-9180.
- 9 (a) Achelle, S.; Rodríguez-López, J.; Katan, C.; Robin-le Guen, F. Luminescence Behavior of Protonated Methoxy-Substituted Diazine Derivatives: Toward White Light Emission. *J. Phys. Chem. C* **2016**, *120*, 26986-26995; (b) Liu, D.; Zhang, Z.; Zhang, H.; Wang, Y. A Novel Approach Towards White Photoluminescence and Electroluminescence by Controlled Protonation of a Blue Fluorophore. *Chem. Commun.* **2013**, *49*, 10001-10003.
- 10 Kato, S.-i.; Yamada, Y.; Hiyoshi, H.; Umezu, K.; Nakamura, Y. Series of Carbazole-Purimidine Conjugates: Syntheses and Electronic, Photophysical, and Electrochemical Properties. *J. Org. Chem.* **2015**, *80*, 9076-9090.
- 11 (a) Klikar, M.; Solanke, P.; Tydlitát, J.; Bureš, F. Alphabet-Inspired Design of (Hetero)Aromatic Push-Pull Chromophores. *Chem. Rec.* **2016**, *6*, 1886-1905; (b) Detert, H.; Lehmann, M.; Meier, H. Star-Shaped Conjugated Systems. *Materials* **2010**, *3*, 3218-3330.
- 12 (a) Meier, H.; Holst, H. C.; Oehlhof, A. Star-Shaped Compounds Having 1,3,5-Triazine Cores. *Eur. J. Org. Chem.* **2003**, 4173-4180; (b) Meier, H.; Karpouk, E.; Holst, H. C. Star-Shaped Push-Pull Compounds Having 1,3,5-Triazine Cores. *Eur. J. Org. Chem.* **2006**, 2609-2617; (c) Jiang, Y.; Wang, Y.; Wang, B.; Yang, J.; He, N.; Qian, S.; Hua, J. Synthesis, Two-Photon Absorption and Optical Limiting Properties of Multi-branched Styryl Derivatives Based on 1,3,5-Triazine. *Chem. Asian J.* **2011**, *6*, 157-165; (d) Wang, Y.; Jiang, Y.; Liu, D.;

Wang, Y.; Wang, G.; Hua, J. Ultrafast Relaxation Processes of Multi-Branched Compounds Based on 1,3,5-Triazine: An Investigation of the Causes of a High Fluorescence Quantum Yield After Modification With Perfluoroalkyl Chains. *J. Lumin.* **2017**, *190*, 89-93.

13 Brunel, J.; Mongin, O.; Jutand, A.; Ledoux, I.; Zyss, J.; Blanchard-Desce, M. Propeller-Shaped Octupolar Molecules Derived From Triphenylbenzene For Nonlinear Optics: Synthesis and Optical Studies. *Chem. Mater.* **2003**, *15*, 4139-4148.

14 (a) Terenziani, F.; Le Droumaguet, C.; Katan, C.; Mongin, O.; Blanchard-Desce, M. Effect of Branching on Two-Photon Absorption in Triphenylbenzene Derivatives. *ChemPhysChem* **2007**, *8*, 723-734; (b) Terenziani, F.; Katan, C.; Badaeva, E.; Tretiak, S.; Blanchard-Desce, M. Enhanced Two-Photon Absorption of Organic Chromophores: Theoretical and Experimental Assessments. *Adv. Mater.* **2008**, *20*, 4641-4678.

15 (a) Itami, K.; Yamazaki, D.; Yoshida, J.-i. Pyrimidine-Core Extended π -Systems: General Synthesis and Interesting Fluorescent Properties. *J. Am. Chem. Soc.* **2004**, *126*, 15396-15397; (b) Achelle, S.; Ramondenc, Y.; Marsais, F.; Plé, N. Star- and Banana-Shaped Oligomers with a Pyrimidine Core: Synthesis and Light-Emitting Properties. *Eur. J. Org. Chem.* **2008**, 3129-3140; (c) Muraoka, H.; Obara, T.; Ogawa, S. Systematic Synthesis, Comparative Studies of the Optical Properties, And the ICT-Based Sensor Properties of a Series of 2,4,6-Tri(5-aryl-2-thienyl)pyrimidines with the D- π -A System. *Tetrahedron Lett.* **2016**, *57*, 3011-3015; (d) Bagley, M. C.; Lin, Z.; Pope, S. J. A. Barium Manganate in Microwave-Assisted Oxidation Reactions: Synthesis of Solvatochromic 2,4,6-Triarylpyrimidines. *Tetrahedron Lett.* **2009**, *50*, 6818-6822.

16 (a) Achelle, S.; Ramondenc, Y.; Dupas, G.; Plé, N. Bis- and Tris(arylethynyl)pyrimidine Oligomers: Synthesis and Light-Emitting Properties. *Tetrahedron* **2008**, *64*, 2783-2791; (b) Malik, I.; Ahmed, Z.; Reimann, S.; Ali, I.; Villinger, A.; Langer, P. Synthesis and Photophysical Properties of Alkynylated Pyrimidines by Site-Selective Sonogashira Reactions

of 2,4,5,6-Tetrachloropyrimidine; First Synthesis of Tetraalkynyl-pyrimidines. *Eur. J. Org. Chem.* **2011**, 2088-2093.

17 (a) Pascal, L.; Vanden Eynde, J.-J.; Van Haverbeke, Y.; Dubois, P.; Michel, A.; Rant, U.; Zojer, E.; Leising, G.; Van Dorn, L. O.; Gruhn, N. E.; Cornil, J.; Brédas, J.-L. Synthesis and Characterization of Novel *para*- and *meta*-Phenylenevinylene Derivatives: Fine Tuning of the Electronic and Optical Properties of Conjugated Materials. *J. Phys. Chem. B* **2002**, *106*, 6442-6450. (b) Zhang, Q.; Luo, L.; Xu, H.; Hu, Z.; Brommesson, C.; Wu, J.; Sun, Z.; Tian, Y.; Uvdal, K. Design, Synthesis, Linear and Nonlinear Photophysical Properties of Novel Pyrimidine-Based Imidazole Derivatives. *New J. Chem.* **2016**, *40*, 3456-3463; (c) Li, L.; Tian, Y.-P.; Yang, J.-X.; Sun, P.-P.; Wu, J.-Y.; Zhou, H.-P.; Zhang, S.-Y.; Jin, B.-K.; Xing, X.-J.; Wang, C.-K.; Li, M.; Cheng, G.-H.; Tang, H.-H.; Huang, W.-H.; Tao, X.-T.; Jiang, M.-H. Facile Synthesis and Systematic Investigations of a Series of Novel Bent-Shaped Two-Photon Absorption Chromophores Based on Pyrimidine. *Chem. Asian J.* **2009**, *4*, 668-680.

18 (a) Achelle, S.; Robin-le Guen, F. 2-Arylvinylpyrimidines versus 4-Arylvinylpyrimidines: Synthesis and Comparison of the Optical Properties. *Tetrahedron Lett.* **2013**, *54*, 4491-4496; (b) Klikar, M.; le Poul, P.; Růžicka, A.; Pytela, O.; Barsella, A.; Dorkenoo, K. D.; Robin-le Guen, F.; Bureš, F.; Achelle, S. Dipolar NLO Chromophores Bearing Diazine Rings as π -Conjugated Linkers. *J. Org. Chem.* **2017**, *82*, 9435-9451.

19 (a) Akdas-Kilig, H.; Roisnel, T.; Ledoux, I.; Le Bozec, H. A New Class of Bipyrimidine-Based Octupolar Chromophores: Synthesis, Fluorescent and Quadratic Nonlinear Optical Properties. *New J. Chem.* **2009**, *33*, 1470-1473; (b) Savel, P.; Akdas-Kilig, H.; Malval, J.-P.; Spangenberg, A.; Roisnel, T.; Fillaut, J.-L. Metal-Induced Dimensionality Tuning in a Series of Bipyrimidine-Based Ligands: a Tool to Enhance Two-Photon Absorption. *J. Mater. Chem. C* **2014**, *2*, 295-305.

- 20 (a) Molander, G. A.; Bernardi, C. R. Suzuki-Miyaura Cross-Coupling Reactions of Potassium Alkenyltrifluoroborates. *J. Org. Chem.* **2002**, *67*, 8424-8429; (b) Yamanaka, H.; Ogawa, S.; Konno, S. Studies on Pyrimidine-Derivatives .18. Reaction of active Methyl-Groups on Pyrimidine N-Oxides. *Chem. Pharm. Bull.* **1980**, *28*, 1526-1533.
- 21 (a) Zielinski, W. Preparation of Pyrimidines and Pyridines From Alkyl Ketones and Nitriles in Presence of Phosphoryl Chloride. *Heterocycles* **1985**, *23*, 1639-1644; (b) Roberts, J. C. A Confirmation of the Structure of 2,6-Dimethyl-4-pyrimidinyl-methyl-lithium and Some Observations on the Condensation of 1,3-Diketones With Acetamide. *J. Chem. Soc.* **1952**, 3065-3068; (c) Giordano, C.; Minisci, F.; Tortelli, V.; Vismara, E. Polar Effects on the Homolytic Methylation of Pyrimidine - Orientation and Polysubstitution. *J. Chem. Soc. Perkin Trans. 2* **1984**, 293-295.
- 22 (a) Armstrong, R. J.; Smith, M. D. Catalytic Enantioselective Synthesis of Atropoisomeric Biaryls: A Cation-Directed Nucleophilic Aromatic Substitution Reaction. *Angew. Chem. Int. Ed.* **2014**, *53*, 12822-12826; (b) Harden, D. B.; Mokrosz, M. J.; Streckowski, L. Addition and Substitution Reactions of Chloropyrimidines With Lithium Reagents. *J. Org. Chem.* **1988**, *53*, 4137-4140.
- 23 Perner, R. J.; Lee, C.-H.; Jiang, M.; Gu, Y.-G.; DiDomenico, S.; Bayburt, E. K.; Alexander, K. M.; Kohlhaas, K. L.; Jarvis, M. F.; Kowaluk, E. L.; Bhagwat, S. S. Synthesis and Biological Evaluation of 6,7-Disubstituted 4-Aminopyrido[2.3-d]pyrimidines as Adenosine Kinase Inhibitors. *Bioorg. Med. Chem. Lett.* **2005**, *15*, 2803-2807.
- 24 (a) Schomaker, J. M.; Delia, T. J. Arylation of Halogenated Pyrimidines via a Suzuki Coupling Reaction. *J. Org. Chem.* **2001**, *66*, 7125-7128; (b) Anderson, S. C.; Handy, S. T. One-Pot Double Suzuki Couplings of Dichloropyrimidines. *Synthesis* **2010**, 221-2724; (c) Delia, T. J.; Schomaker, J. M.; Kalinda, A. S. The Synthesis of substituted Phenylpyrimidines via Suzuki Coupling Reactions. *J. Heterocycl. Chem.* **2006**, *43*, 127-131.

- 25 Tang, C.; Zhang, Q.; Li, D.; Zhang, J.; Shi, P.; Li, S.; Wu, J.; Tian, Y. Synthesis, Crystal Structures, Two-Photon Absorption and Biological Imaging Application of Two Novel Bent-Shaped Pyrimidine Derivatives. *Dyes Pigm.* **2013**, *99*, 20-28.
- 26 Eaton, D. F. Reference Materials for Fluorescence Measurement. *Pure Appl. Chem.* **1988**, *60*, 1107–1114.
- 27 Reichardt, C. Solvatochromic Dyes as Solvent Polarity Indicators. *Chem. Rev.* **1994**, *94*, 2319-2358.
- 28 (a) Lartia, R.; Alain, C.; Bordeau, G.; Schmidt, F.; Fiorini-Debuisschert, C.; Charra, F.; Teulade-Fichou, M.-P. Synthetic Strategies to Derivatizable Triphenylamine Displaying High Two-Photon Absorption. *J. Org. Chem.* **2008**, *73*, 1732-1744; (b) Katan, C.; Charlot, M.; Mongin, O.; Le Droumaguet, C.; Jouikov, V.; Terenziani, F.; Badaeva, E.; Tretiak, S.; Blanchard-Desce, M. Simultaneous Control of Emission Localization and Two-Photon Absorption Efficiency in Dissymmetrical Chromophores. *J. Phys. Chem. B* **2010**, *114*, 3152-3169; (c) Merkt, F. K.; Höwedes, S. P.; Gers-Panther, C. F.; Gruber, I.; Janiak, C.; Müller, T. J. J. Three-Component Activation/Alkynylation/Cyclocondensation (AACC) Synthesis of Enhanced Emission Solvatochromic 3-Ethynylquinoxalines. *Chem. Eur. J.* **2018**, *24*, 8114-8125; (d) Panthi, K.; Adhikari, R. M.; Kinstle, T. H. Aromatic Fumaronitrile Core-Based Donor-Linker-Acceptor-Linker-Donor (D-pi-A-pi-D) Compounds: Synthesis and Photophysical Properties. *J. Phys. Chem. A* **2010**, *114*, 4542-4549.
- 29 Gaussian 16, Revision A.03, Frisch, M. J.; Trucks, G. W.; Schlegel, H. B.; Scuseria, G. E.; Robb, M. A.; Cheeseman, J. R.; Scalmani, G.; Barone, V.; Petersson, G. A.; Nakatsuji, H.; Li, X.; Caricato, M.; Marenich, A. V.; Bloino, J.; Janesko, B. G.; Gomperts, R.; Mennucci, B.; Hratchian, H. P.; Ortiz, J. V.; Izmaylov, A. F.; Sonnenberg, J. L.; Williams-Young, D.; Ding, F.; Lipparini, F.; Egidi, F.; Goings, J.; Peng, B.; Petrone, A.; Henderson, T.; Ranasinghe, D.; Zakrzewski, V. G.; Gao, J.; Rega, N.; Zheng, G.; Liang, W.; Hada, M.; Ehara, M.; Toyota, K.;

Fukuda, R.; Hasegawa, J.; Ishida, M.; Nakajima, T.; Honda, Y.; Kitao, O.; Nakai, H.; Vreven, T.; Throssell, K.; Montgomery Jr. J. A.; Peralta, J. E.; Ogliaro, F.; Bearpark, M. J.; Heyd, J. J.; Brothers, E. N.; Kudin, K. N.; Staroverov, V. N.; Keith, T. A.; Kobayashi, R.; Normand, J.; Raghavachari, K.; Rendell, A. P.; Burant, J. C.; Iyengar, S. S.; Tomasi, J.; Cossi, M.; Millam, J. M.; Klene, M.; Adamo, C.; Cammi, R.; Ochterski, J. W.; Martin, R. L.; Morokuma, K.; Farkas, O.; Foresman, J. B. and Fox, D. J. Gaussian, Inc., Wallingford CT, 2016.

30 (a) Klikar, M.; Kityk, I. V.; Kulwas, D.; Mikysek, T.; Pytela, O.; Bureš, F. Multipodal Arrangement of Push-Pull Chromophores: a Fundamental Parameter Affecting Their Electronic and Optical Properties. *New J. Chem.* **2017**, *41*, 1459-1472; (b) Klikar, M.; Seintis, K.; Polyzos, I.; Pytela, O.; Mikysek, T.; Almonasy, N.; Fakis, M.; Bureš, F. Star-Shaped Push-Pull Molecules with a Varied Number of Peripheral Acceptors: An Insight into Their Optoelectronic Features. *ChemPhotoChem* **2018**, *2*, 465-474; (c) Seintis, K.; Agathangelou, D.; Cvejn, D.; Almonasy, N.; Bureš, F.; Giannetas, V.; Fakis, M. Femtosecond to Nanosecond Studies of Octupolar Molecules and Their Quadrupolar and Dipolar Analogues. *Phys. Chem. Chem. Phys.* **2017**, *19*, 16485-16497.

31 Sakamoto, T.; Tanhji, K.-I.; Niitsuma, S.; Ono, T.; Yamanaka, H. Studies on Pyrimidine Derivatives .20. Synthetic Utility of Hydroxymethylpyrimidines and Related-Compounds. *Chem. Pharm. Bull.* **1980**, *28*, 3362–3368.

32 Stanek, J.; Caravatti, G.; Capraro, H.-G.; Furet, P.; Mett, H.; Schneider, P.; Regenass, U. S-Adenosylmethionine Decarboxylase Inhibitors - New Aryl and Heteroaryl Analogs of Methylglyoxal Bis(guanyldrazone). *J. Med. Chem.* **1993**, *36*, 46–54.